

**Specification and
characterization methods
for nonwoven “E” glass mat**

PUBLICLY AVAILABLE SPECIFICATION



INTERNATIONAL
ELECTROTECHNICAL
COMMISSION



Reference number
IEC/PAS 62212

IECNORM.COM: Click to view the full PDF of IEC PAS 62212:2001



*THE INSTITUTE FOR
INTERCONNECTING
AND PACKAGING
ELECTRONIC CIRCUITS*

IPC-4130

Specification and Characterization Methods for Nonwoven "E" Glass Mat

IPC-4130

September 1998

A standard developed by the Institute for Interconnecting
and Packaging Electronic Circuits

2215 Sanders Road
Northbrook, Illinois
60062-6135

Tel 847 509.9700
Fax 847 509.9798
URL: www.ipc.org

IECNORM.COM: Click to view the full PDF of IEC PAS 62212:2001

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATION AND CHARACTERIZATION METHODS
FOR NONWOVEN “E” GLASS MAT

FOREWORD

A PAS is a technical specification not fulfilling the requirements for a standard, but made available to the public and established in an organization operating under given procedures.

IEC-PAS 62212 was submitted by the IPC (The Institute for Interconnecting and Packaging Electronic Circuits) and has been processed by IEC technical committee 52: Printed circuits. It will be further processed by IEC TC 91: Electronics assembly technology.

The text of this PAS is based on the following document:

This PAS was approved for publication by the P-members of the committee concerned as indicated in the following document:

Draft PAS	Report on voting
52/870/PAS	52/880/RVD

Following publication of this PAS, the technical committee or subcommittee concerned will investigate the possibility of transforming the PAS into an International Standard.

An IEC-PAS licence of copyright and assignment of copyright has been signed by the IEC and IPC and is recorded at the Central Office.

- 1) The IEC (International Electrotechnical Commission) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of the IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, the IEC publishes International Standards. Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. The IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of the IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested National Committees.
- 3) The documents produced have the form of recommendations for international use and are published in the form of standards, technical specifications, technical reports or guides and they are accepted by the National Committees in that sense.
- 4) In order to promote international unification, IEC National Committees undertake to apply IEC International Standards transparently to the maximum extent possible in their national and regional standards. Any divergence between the IEC Standard and the corresponding national or regional standard shall be clearly indicated in the latter.
- 5) The IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with one of its standards.
- 6) Attention is drawn to the possibility that some of the elements of this PAS may be the subject of patent rights. The IEC shall not be held responsible for identifying any or all such patent rights.

Acknowledgment

Any standard involving a complex technology draws material from a vast number of sources. While the principal members of the Nonwoven Glass Reinforcement Task Group (3-12f) are shown below, it is not possible to include all of those who assisted in the evolution of this standard. To each of them, the members of the IPC extend their gratitude.

Base Materials Committee	Nonwoven Glass Reinforcement Task Group	Technical Liaison of the IPC Board of Directors
Chairman D. Sober isola/USA	Chairman D. Lockyer Crane & Co.	J. Donaghy Sheldahl
Nonwoven Glass Reinforcement Task Group		
Bruce Andrews, Crane & Company Inc.	Terry Fischer, Hitachi Chemical Co. America	Joel Murray, Clark-Schwebel Inc.
Mike Bryant, BGF Industries Inc.	Jeffrey Gleim, P.H. Glatfelter Co.	Thomas Nowak, Nowak & Associates
H. Landis Carter, JPS Glass and Industrial Fabrics Corp.	Florian Gunkle, AlliedSignal Laminate Systems	Paul Reichenbacher, AlliedSignal Laminate Systems
Yong Deng, Owens-Corning Fiberglass Corp.	Ulrich Kempf, FiberMark Inc.	Tony Senese, Taconic
Nitin Desai, Motorola Inc.	Rodney Komlenic, Ahlstrom Paper Group	William Shaw, FiberMark Inc.
Howard Elliott, Polyclad Laminates Inc.	Robert Konsowitz, GIL Technologies	Lowell Sherman, Defense Supply Center Columbus DSCC
Werner Engelmaier, Engelmaier Associates Inc.	Dennis Lockyer, Crane & Company Inc.	Douglas Sober, isolaUSA
James Feeney, Morton Electronic Materials	P. Douglas Lyle, Owens-Corning Fiberglass Corp.	Xie Xiaoyan, Dongguan Shengyi Copper Clad Laminate Co. Ltd.

Table of Contents

1 METHODOLOGY	1	4 QUALITY ASSURANCE	3
1.1 Scope.....	1	4.1 Responsibility for Inspection.....	3
1.2 Purpose.....	1	4.1.1 Test Equipment and Inspection Facilities	3
1.3 Classification.....	1	4.1.2 Standard Laboratory Conditions.....	3
2 APPLICABLE DOCUMENTS	1	4.2 Preparation of Samples.....	3
2.1 IPC.....	1	4.3 Inspection Procedure.....	3
2.2 TAPPI.....	1	4.3.1 Classification of Major and Minor Visual Defects	3
3 REQUIREMENTS	1	4.3.2 Sampling Plans	3
3.1 Terms and Definitions.....	1	4.4 Acceptability Quality Level.....	3
3.1.1 Bagginess	1	4.5 Statistical Process Control (SPC).....	3
3.1.2 Binder.....	1	5 PREPARATION FOR DELIVERY	3
3.1.3 Bundles.....	1	5.1 Roll Size.....	3
3.1.4 Caliper Variation.....	1	5.1.1 Roll Length.....	3
3.1.5 Conducting Particles.....	1	5.1.2 Roll Width.....	3
3.1.6 Dents	1	5.2 Splices	3
3.1.7 Dirt	1	5.3 Preservation and Packaging.....	4
3.1.8 Edge Tear/Damaged Roll Edge.....	1	5.4 Packing.....	4
3.1.9 Holes/Thin Spots.....	1	5.5 Labeling.....	4
3.1.10 Poor Formation	1	6 NOTES	4
3.1.11 Soft Roll/Telescoping	1	6.1 Ordering Data	4
3.1.12 Weight Variation	1		
3.1.13 Wrinkles/Folds	1		
3.2 Physical Requirements	1		
3.2.1 Product	1		
3.2.2 "E" Glass Fibers	2		
3.2.3 Diameter and Range	2		
3.3 Visual Requirements.....	2		
3.3.1 Visual Appearance Procedures.....	2		
3.3.2 Visual Appearance Defects.....	2		
3.4 Dimensional Requirements.....	2		
3.4.1 Roll Length.....	2		
3.4.2 Roll Width.....	2		
		Tables	
		Table 3-1 Chemical Compositions.....	2
		Table 3-2 Diameter and Range	2
		Table 3-3 Defect Classifications.....	2
		Table 3-4 TAPPI Test Methods and Procedures.....	2
		Table 4-1 General Inspection	3
		Specification sheets	5

This Page Intentionally Left Blank

Specification and Characterization Methods for Nonwoven “E” Glass Mat

1 METHODOLOGY

1.1 Scope This specification covers mat made from nonwoven “E” glass fibers intended as a reinforcing material in laminated plastics for electrical and electronic use.

1.2 Purpose This specification determines the nomenclature, definitions, general comments, and physical requirements for mat made from nonwoven “E” glass.

1.3 Classification This specification provides physical characteristics of the mat required to meet the design and performance requirements of the PWBs.

2 APPLICABLE DOCUMENTS

2.1 IPC¹

IPC-T-50 Terms and Definitions for Interconnecting and Packaging Electronic Circuits

IPC-PC-90 General Requirements for Implementation of Statistical Process Control

2.2 TAPPI²

T 251 wd ³ -96	Air Permeability of Porous Papers, Fabrics, and Pulp
T 411 om-89	Thickness (Caliper) of Paper, Paperboard, and Combined Board
T 456 om-87	Wet Tensile Breaking Strength of Paper and Paperboard
T 1007 om-92	Sample Location
T 1008 om-92	Test Conditions for Fiberglass Mat Test Methods
T 1009 om-92	Tensile Strength and Elongation at Break
T 1011 om-92	Basis Weight of Fiberglass Mats
T 1013 om-92	Loss of Ignition of Fiberglass Mats

3 REQUIREMENTS

3.1 Terms and Definitions The definitions and terms **shall** be in accordance with IPC-T-50, TAPPI documents, and those stated in 3.1.1 through 3.1.13.

3.1.1 Bagginess Material that is distorted, stretched, or deformed in the middle or along the edges.

3.1.2 Binder A thermoset or thermoplastic resin used to hold the glass fibers together and provide mechanical strength to the nonwoven mat.

3.1.3 Bundles Undispersed fiber bundles.

3.1.4 Caliper Variation Sheet is of uneven thickness in the width and length, exceeding the product's specification.

3.1.5 Conducting Particles Small foreign particles capable of conducting current.

3.1.6 Dents Indentations in the surface of the mat or in the edge of the roll.

3.1.7 Dirt Small dark particles of foreign origin (i.e., floor dirt or other visible contaminants).

3.1.8 Edge Tear/Damaged Roll Edge Tears and/or damage to the edge of the mat.

3.1.9 Holes/Thin Spots An area in the mat where few or no fibers are present.

3.1.10 Poor Formation Very uneven distribution of fibers in the mat resulting in a rough surface or appearance.

3.1.11 Soft Roll/Telescoping Roll that has been loosely wound, resulting in an uneven side-to-side hardness and/or evenness.

3.1.12 Weight Variation Basis weight variation in the width and length exceeding the product's specification.

3.1.13 Wrinkles/Folds A permanent fold, crease, or ridge in the mat, generally in the machine direction, occurring during processing or rewinding.

3.2 Physical Requirements

3.2.1 Product Typical physical requirements of nonwoven “E” glass mats are provided at the end of this specification in the form of specification sheets. The specification sheets may not cover all of the commercially available

1. IPC, 2215 Sanders Road, Northbrook, IL 60062, 847-509-9700, <http://www.ipc.org>

2. TAPPI, 1-800-322-8686 (U.S.), 1-800-446-9431 (Canada), +1-770-209-7303 (International), or visit <http://www.tappi.org> for a list of local TAPPI divisions.

3. Withdrawn Method – Available upon request from TAPPI.

nonwoven glass used in base material manufacturing. This specification is not designed to preclude their use in these applications, provided the requirements of Section 3 are met. New specification sheets **shall** be added as materials and data are made available.

3.2.2 “E” Glass Fibers “E” glass fibers **shall** have a chemical composition by weight within the limits of Table 3-1.

Table 3-1 Chemical Compositions

Composition	Range
Silicon dioxide	52-56%
Aluminum oxide	12-16%
Boron oxide	5-10%
Sodium oxide and potassium oxide	0-2%
Magnesium oxide.	0-5%
Calcium oxide	0-0.8%
Titanium dioxide	0-1.5%
Iron oxide	0.5-0.4%
Iron	0-1%

3.2.3 Diameter and Range The nominal filament diameter and the range of filament diameter averages in μm are as shown in Table 3-2.

Table 3-2 Diameter and Range

Code	Diameter (μm)	Range (μm)
D	5	4.83 - 5.83
DE	6	5.84 - 6.85
E	7	6.35 - 7.61
G	9	8.89 - 10.15
H	11	10.16 - 11.42
K	13	12.7 - 14.0

3.3 Visual Requirements

3.3.1 Visual/Appearance Procedures Mats **shall** be inspected across the full width of the sheet. The mat **shall** be of uniform appearance and formation. The lighting source should be mounted behind the viewing surface of the mat so as to illuminate the mat from the back with perpendicular light.

3.3.2 Visual/Appearance Defects Count all defects except where two or more defects represent a single local condition (all within one linear meter). In this case, count only the more serious defect as one defect. A continuous defect is counted as one defect for each linear meter or fraction thereof in which it appears. Classify the defects as listed in Table 3-3. Table 3-4 lists the test methods and

procedures used to determine values found in the applicable specification sheets.

Table 3-3 Defect Classifications

Defect	Major	Minor
Bagginess		•
Weight Variation	•	
Caliper Variation	•	
Conducting Particles	•	
Edge Tears	•	
Dents		•
Dirt	•	
Wrinkles/Folds	•	
Holes	•	
Poor Formation	•	
Bundles		•
Soft Roll/Telescoping		•

Table 3-4 TAPPI Test Methods and Procedures

Test Method	Procedure Number
Sample Location	T 1007
Test Conditions	T 1008
Basis Weight	T 1011
Tensile Strength	T 1009
Solvent Tensile	T 456 ⁴
Caliper	T 411
Loss on Ignition (LOI)	T 1013
Porosity	T 251
Wet-Out ⁵	

3.4 Dimensional Requirements

3.4.1 Roll Length The roll length **shall** be measured by the clock method or equivalent. In the clock method, the measuring device consists of a wheel or pair of wheels mounted on a free-running axle, connected to a counting mechanism graduated to read in meters. The surface of the wheels is to be covered with a friction material to prevent slippage. The circumference of the wheel is to be known and synchronized with a mechanism to read in meters.

The measuring device is to be mounted in such a way that movement of the mat through the machine will turn the wheels. The roll will be measured from beginning to end and the length reported to the nearest meter.

3.4.2 Roll Width Place the roll of mat in the horizontal position. Measure the width to within 3.2 mm perpendicular to the edges using steel tape.

4. Substitute solvent for water saturation. Type of solvent should be agreed upon between user and supplier.

5. It is recommended that the user request samples of the nonwoven mat from the supplier to evaluate wet-out characteristics and to ensure compatibility with current process and resin systems.

4 QUALITY ASSURANCE

4.1 Responsibility for Inspection Unless otherwise specified in the purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the purchase order, the supplier may use their own or any other facility suitable for the performance of the inspection requirements herein, unless disapproved by the procuring authority. The procuring authority reserves the right to perform any of the inspections set forth in the specification, where such inspections are deemed necessary, to assure supplies and service is performed to the prescribed requirements.

4.1.1 Test Equipment and Inspection Facilities Test and measuring equipment and inspection facilities of sufficient accuracy, quality, and quantity to permit performance of the required inspection **shall** be established and maintained by the supplier. The supplier **shall** perform the establishment and maintenance of a calibration system to control the accuracy of the measuring and test equipment.

4.1.2 Standard Laboratory Conditions Unless otherwise specified herein, all inspections **shall** be performed in accordance with standard TAPPI procedures (see Table 3-4). If a referee method is required, it **shall** be agreed upon between user and supplier.

4.2 Preparation of Samples Unless otherwise specified herein, samples **shall** be prepared in accordance with standard TAPPI procedures (see Table 3-4). If a referee method is required, it **shall** be as agreed upon between user and supplier.

4.3 Inspection Procedure All reels **shall** be inspected per 4.3.1. Visual defects are classified in Table 3-3.

4.3.1 Classification of Major and Minor Visual Defects

4.3.1.1 Major Defect A major defect is a defect that is likely to result in failure, or to materially reduce the usability of the unit of product for its intended purpose (see Table 3-3).

4.3.1.2 Minor Defect A minor defect is a defect that is not likely to materially reduce the usability of the unit of product for its intended purpose (see Table 3-3).

4.3.2 Sampling Plans Sampling plans sufficient to ensure an acceptable quality **shall** be used (see Table 4-1).

4.4 Acceptability Quality Level No one meter will be penalized with more than one major defect. A continuous defect **shall** be counted as one defect for each meter or fraction thereof in which it occurs. Latent defects or defects

Table 4-1 General Inspection

Number of Rolls Shipped	Minimum Number of Rolls Inspected
2-8	2
9-15	4
16-25	6
26-50	16
51-91	23
91-150	38

that appear during and after treating can occur to make the product unacceptable for its intended use. The acceptable level of these defects and the resolution of any rejects arising must be negotiated between user and supplier.

4.5 Statistical Process Control (SPC) SPC utilizes systematic statistical techniques to analyze a process or its outputs. The purpose of these analyses is to take appropriate actions to achieve and maintain a state of statistical control, and to assess and improve process capability. The primary goal of SPC is to continually reduce variation in processes, products, or services in order to provide product meeting or exceeding real or important customer requirements.

Implementation of SPC **shall** be in accordance with IPC-PC-90.

Depending on the progress made in implementing SPC on a particular product, an individual supplier may demonstrate compliance to specification with any of the following:

- Quality conformance evaluations
- End-product control
- In-process product control
- Process parameter control

5 PREPARATION FOR DELIVERY

5.1 Roll Size The outside diameter, width, and core size **shall** conform to the customer's specification.

5.1.1 Roll Length Roll length **shall** be determined in accordance with 3.4.1 and **shall** be as specified on the purchase order (min-max roll length). Roll diameter may be substituted for roll length as a means of specifying roll size.

5.1.2 Roll Width Roll width **shall** be determined in accordance with 3.4.2 and **shall** be as specified on the purchase order. The width of the mat **shall** be within -0 mm + 6.4 mm of the value specified.

5.2 Splices There **shall** be a maximum of one splice per roll, or as otherwise agreed upon between user and supplier or specified per purchase order. All splices **shall** be flagged

and compatible with resin solvents. Splices **shall** not lose strength and **shall** withstand treater stresses.

5.3 Preservation and Packaging Preservation and packaging **shall** be in such a manner as to ensure delivery in a condition that will pass the requirements of this specification.

5.4 Packing Packing **shall** be as specified.

5.5 Labeling In addition to any special labeling required by the contract or order, each roll **shall** be labeled clearly to assure product identity.

6 NOTES

6.1 Ordering Data The purchase order should specify the following:

- (a) Product grade code designation
- (b) Basis weight required
- (c) Roll size: outside diameter, width, and length
- (d) Core inside diameter size (i.e., 76.2 mm or 152.4 mm I.D.)
- (e) Customer purchase order number
- (f) Special labeling instructions
- (g) Special packing instructions
- (h) Ship-to address
- (i) Purchaser's part number, if required
- (j) Quantity: total weight and/or length

Specification Sheets for Nonwoven “E” Glass Mat

Specification Sheet #	Description
01	Glass Mat Epoxy 9.0 μm x 6.5 mm
02	Glass Mat Epoxy 11.0 μm x 6.5 mm
03	Glass Mat Epoxy 7.5 μm x 6.5 mm
04	Glass Mat Polyvinyl Alcohol 6.5 μm x 6.5 mm
05	Glass Mat Polyvinyl Alcohol 6.5 μm x 6.5 mm

Withdrawing
IECNORM.COM: Click to view the full PDF of IEC PAS 62212:2001

Specification Sheet

Specification Sheet : IPC-4130/01
 # Reinforcement : Glass Mat
 Binder Identification : Epoxy
 Fiber Identification : 9.0 μm x 6.5 mm

Nonwoven "E" Glass Mat Requirements

Requirement	Specification	Units	Test Method	Ref. Para
1. Basis Weight nominal minimum maximum	— 80.0 76.0 84.0	g/m^2	T 1011	4.1.2 3.1.12
2. Caliper nominal minimum maximum	— .41 .37 .45	mm	T 411	4.1.2 3.1.4
3. LOI nominal minimum maximum	— 10.0 8.0 12.0	%	T 1013	4.1.2
4. Tensile MD CD	— ≥ 5.9 ≥ 2.9	kg/15 mm	T 1009	4.1.2
5. Solvent Tensile MD	— ≥ 4.7	kg/15 mm	T 456*	4.1.2
6. Porosity nominal minimum maximum	— 241 216 267	$\text{cm}^3/\text{sec}/\text{cm}^2$ @12.7 mm pressure drop	T 251	4.1.2

Specifications should be changed to suit buyer's needs.

Specification Sheet

Specification Sheet : IPC-4130/02
 # Reinforcement : Glass Mat
 Binder Identification : Epoxy
 Fiber Identification : 11.0 μm x 6.5 mm

Nonwoven "E" Glass Mat Requirements

Requirement	Specification	Units	Test Method	Ref. Para
1. Basis Weight nominal minimum maximum	— 100.0 95.0 105.0	g/m^2	T 1011	4.1.2 3.1.12
2. Caliper nominal minimum maximum	— .51 .46 .56	mm	T 411	4.1.2 3.1.4
3. LOI nominal minimum maximum	— 10.0 8.0 12.0	%	T 1013	4.1.2
4. Tensile MD CD	— ≥ 7.1 ≥ 3.5	kg/15 mm	T 1009	4.1.2
5. Solvent Tensile MD	— ≥ 5.7	kg/15 mm	T 456*	4.1.2
6. Porosity nominal minimum maximum	— 267 241 292	$\text{cm}^3/\text{sec}/\text{cm}^2$ @12.7 mm pressure drop	T 251	4.1.2

Specifications should be changed to suit buyer's needs.

Specification Sheet

Specification Sheet : IPC-4130/03
 # Reinforcement : Glass Mat
 Binder Identification : Epoxy
 Fiber Identification : 7.5 μm x 6.5 mm

Nonwoven "E" Glass Mat Requirements

Requirement	Specification	Units	Test Method	Ref. Para
1. Basis Weight nominal minimum maximum	— 105.0 100.0 105.0	g/m^2	T 1011	4.1.2 3.1.12
2. Caliper nominal minimum maximum	— .56 .50 .62	mm	T 411	4.1.2 3.1.4
3. LOI nominal minimum maximum	— 10.0 8.0 12.0	%	T 1013	4.1.2
4. Tensile MD CD	— ≥ 6.5 ≥ 3.2	kg/15 mm	T 1009	4.1.2
5. Solvent Tensile MD	— ≥ 5.2	kg/15 mm	T 456*	4.1.2
6. Porosity nominal minimum maximum	— 127 102 152	$\text{cm}^3/\text{sec}/\text{cm}^2$ @12.7 mm pressure drop	T 251	4.1.2

Specifications should be changed to suit buyer's needs.

Specification Sheet

Specification Sheet : IPC-4130/04
 # Reinforcement : Glass Mat
 Binder Identification : Polyvinyl Alcohol
 Fiber Identification : 6.5 μm x 6.5 mm

Nonwoven "E" Glass Mat Requirements

Requirement	Specification	Units	Test Method	Ref. Para
1. Basis Weight nominal minimum maximum	— 105.0 100.0 105.0	g/m^2	T 1011	4.1.2 3.1.12
2. Caliper nominal minimum maximum	— .56 .50 .62	mm	T 411	4.1.2 3.1.4
3. LOI nominal minimum maximum	— 7.0 5.0 9.0	%	T 1013	4.1.2
4. Tensile MD CD	— ≥ 5.3 ≥ 2.7	kg/15 mm	T 1009	4.1.2
5. Solvent Tensile MD	— ≥ 4.2	kg/15 mm	T 456*	4.1.2
6. Porosity nominal minimum maximum	— 124 102 152	$\text{cm}^3/\text{sec}/\text{cm}^2$ @12.7 mm pressure drop	T 251	4.1.2

Specifications should be changed to suit buyer's needs.