
**Paper, board and pulps — Measurement
of diffuse radiance factor**

*Papier, carton et pâtes — Mesurage du facteur de luminance
énergétique diffuse*

STANDARDSISO.COM : Click to view the full PDF of ISO 2469:2007



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2469:2007



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus	3
6 Photometric calibration of the instrument and its working standards	4
7 Sampling	5
8 Preparation of the test pieces	5
9 Procedure	5
10 Calculation and expression of results	6
11 Precision	6
12 Test report	6
Annex A (normative) Instruments for the measurement of radiance factor	8
Annex B (normative) Calibration service — Photometric calibration	11
Annex C (normative) Calibration service — UV-adjustment	13
Annex D (informative) Measurement uncertainty	15
Annex E (informative) Radiance and reflectance	18
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2469 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This fourth edition of ISO 2469 cancels and replaces the third edition (ISO 2469:1994) and ISO 2469:1994/Cor.1:1998, which have been technically revised. Primarily, certain instrumental features and computational routines are more rigorously defined in order to meet the requirements of technological advances and in order to ensure a high precision and reproducibility in the measurement results.

In addition, the property mentioned in the title has been changed from “diffuse reflectance factor” to “diffuse radiance factor” as an acknowledgement of the fact that many grades of paper now contain added fluorescent whitening agents. For any given material, the total radiance factor is the sum of the reflected radiance factor and the luminescent radiance factor, and it is this total property which is the subject of this International Standard. For pulps and papers not containing any fluorescent component, the radiance factor and the reflectance factor are synonymous, see Annex E.

Introduction

The radiance factor depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. The diffuse radiance factor as defined by this International Standard is determined using instruments having the characteristics given in Annex A and calibrated according to the procedure specified in Annex B.

The radiance factor is the sum of the reflected radiance factor and the luminescent radiance factors, and the radiance factor of a luminescent (fluorescent) object is dependent on the spectral power distribution of the illumination. The content of UV radiation in the illumination must therefore be set to a specified level if adequately accurate measurements are to be carried out on fluorescent objects. The preparation of fluorescent reference standards to enable this adjustment to be made is described in Annex C. The use of these fluorescent reference standards is described in detail in the International Standards describing the measurement of the properties of the materials containing fluorescent whitening agents.

The spectral radiance factor or the weighted radiance factor applicable to one or several specified wavelength bands is often used to characterize the properties of pulp, paper and board. Examples of radiance factors associated with specified wavelength bands are the ISO brightness (diffuse blue radiance factor) and the luminance factor.

The radiance factor or reflectance factor is also used as the basis for calculating optical properties, such as opacity, colour, whiteness and the Kubelka-Munk scattering and absorption coefficients. These various properties are specified in specific International Standards, for all of which this International Standard is the primary normative reference.

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 2469:2007

Paper, board and pulps — Measurement of diffuse radiance factor

1 Scope

This International Standard describes the general procedure for measuring the diffuse radiance factor of all types of pulp, paper and board. More particularly, it specifies in detail in Annex A the characteristics of the equipment to be used for such measurements, and in Annex B the procedures to be used for calibrating that equipment.

This International Standard may be used to measure the radiance factors and related properties of materials containing fluorescent whitening agents, provided that the UV radiation content in the illumination has been adjusted to the level specified in the specific International Standard describing the measurement of the property in question.

This International Standard describes in Annex C the preparation of fluorescent reference standards, although the procedures for using these standards are not included, since their use is described in detail in the specific International Standards describing the measurement of the properties of materials containing fluorescent whitening agents.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

ASTM E308-06, *Standard Practice for Computing the Colors of Objects by Using the CIE System*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 radiance factor

β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that of the perfect reflecting diffuser under the same conditions of illumination

NOTE For luminescent (fluorescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_S , and the luminescent radiance factor, β_L , so that:

$$\beta = \beta_S + \beta_L$$

For non-fluorescent materials, the reflected radiance factor, β_S , is numerically equal to the reflectance factor, R .

3.2

diffuse radiance factor

R

ratio of the radiation reflected and emitted from a body to that reflected from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 This International Standard prescribes diffuse illumination and normal detection in an instrument constructed and calibrated in accordance with the provisions of this standard.

3.3

intrinsic radiance factor

R_{∞}

diffuse radiance factor of a layer or pad of material thick enough to be opaque, i.e., such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance factor

NOTE The radiance factor of a single non-opaque sheet is dependent on the background and is not a material property.

3.4

reflectance factor

ratio of the radiation reflected by a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that reflected by the perfect reflecting diffuser under the same conditions of illumination

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 This term may be used only when it is known that the test material exhibits no luminescence (fluorescence).

3.5

diffuse reflectance factor

R

ratio of the reflection from a body to that from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 This International Standard specifies diffuse illumination and normal detection in an instrument constructed and calibrated in accordance with the provisions of this standard.

3.6

intrinsic reflectance factor

R_{∞}

diffuse reflectance factor of a layer or pad of material thick enough to be opaque, i.e., such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

NOTE The reflectance factor of a single non-opaque sheet is dependent on the background and is not a material property.

3.7

ISO reference standard of level 1

IR1

the perfect reflecting diffuser (see CIE publication 17.4, No 845.04.54); an ideal spectrally uniform isotropic Lambertian diffuser with a reflectance equal to 1 at all wavelengths

NOTE Reflectance is defined as the ratio of the reflected to the incident radiation, see Annex E.

3.8**ISO reference standard of level 2****IR2**

standard whose radiance factors have been determined by a standardizing laboratory in relation to the IR1 as defined by ISO 4094

NOTE This International Standard refers to two types of IR2.

A non-fluorescent IR2 whose spectral reflectance factors have been determined by a standardizing laboratory in relation to the IR1. A non-fluorescent IR2 is used to calibrate the photometric scale of an authorized laboratory's reference instrument.

A fluorescent IR2 whose spectral radiance factors corresponding to a specified CIE illuminant have been determined by a standardizing laboratory. A fluorescent IR2 standard is used to adjust the UV level of an authorized laboratory's reference instrument.

3.9**ISO reference standard of level 3****IR3**

standard whose radiance factors have been determined by an authorized laboratory in relation to an IR2, as defined by ISO 4094

NOTE This International Standard refers to two types of IR3.

A non-fluorescent IR3 whose spectral reflectance factors have been determined by an authorized laboratory in relation to the IR2. A non-fluorescent IR3 is used to calibrate the photometric scale of a testing laboratory's reference instrument.

A fluorescent IR3 whose calibration values have been determined an authorized laboratory in relation to the IR2. A testing laboratory uses a fluorescent IR3 to adjust the relative amount of UV radiation incident on the sample to a specified level.

4 Principle

A test piece is irradiated diffusely in a standard instrument and the light reflected (and emitted as a result of fluorescence) in a direction normal to the surface is passed to a detection system. This detection system may consist either of a defined optical filter and photodetector or of an array of photodetectors where each detector responds to a specific effective wavelength. The desired radiance factors are determined directly from the output from the photodetector in the former case or by calculation from the detector array outputs using appropriate weighting functions in the latter case.

5 Apparatus

5.1 Reflectometer, having the geometric, spectral and photometric characteristics described in Annex A.

5.2 Reference standards for calibration of the instrument and the working standards, a non-fluorescent reference standard for photometric calibration of the instrument and its working standards, issued by an ISO/TC 6 authorized laboratory and fulfilling the requirements for an ISO reference standard of level 3 (see 3.9) as specified in Annex B.

Use reference standards sufficiently frequently to ensure satisfactory calibration.

NOTE If fluorescent materials are to be measured, a fluorescent reference standard issued by an ISO/TC 6 authorized laboratory is required to enable the UV-content of the illumination to be adjusted to correspond to the appropriate CIE illuminant, as specified in Annex C. The use of these fluorescent reference standards is described in the International Standards concerned.

5.3 Two non-fluorescent working standards, of opal glass, ceramic or other suitable material with flat surfaces.

NOTE In some instruments, the function of the primary working standard (see 6.3) may be fulfilled by a built-in internal standard.

For measurements on fluorescent materials, which require a fluorescent reference standard (see 5.2) to enable the UV-content of the illumination to be adjusted, stable fluorescent working standards of plastic or other material incorporating a fluorescent whitening agent are required. These working standards are described in the relevant International Standards.

5.4 Black cavity, for calibration or validation of the low end of the photometric scale. This black cavity shall have a radiance factor which does not differ from its nominal value by more than 0,2 percentage points at all wavelengths. The black cavity should be stored upside-down in a dust-free environment or with a protective cover. During calibration, the instrument shall be adjusted to the nominal value of the black cavity.

It is not yet possible to institute a system of reference standards to enable testing laboratories to check the reflectance factor of the black cavity. At the time of delivery, the level should be guaranteed by the instrument maker. Questions concerning the use and condition of the black cavity should be resolved by contacting the instrument maker.

6 Photometric calibration of the instrument and its working standards

6.1 Calibration of the instrument

Using the procedure appropriate to the instrument, calibrate the instrument with an IR3. Make a measurement on the IR3 in order to check that the calibration is satisfactory. The deviation between the measured and the assigned brightness and/or tristimulus values of the IR3 used for the primary calibration should not exceed 0,05 percentage points.

NOTE Although barium sulfate powders for pressing tablets are commercially available for which the absolute spectral radiance factors are given on the container, these values are not considered to be traceable according to the principles of modern metrology, and tablets based on barium sulfate powder are not considered to be suitable for use as an IR3 as required by this International Standard.

All calibrations are thus related to the IR1 through a calibration chain comprising an IR2 and an IR3 to which absolute values have been assigned respectively by a standardizing laboratory and by an authorized laboratory using an instrument conforming to this International Standard.

Handle each IR3 carefully and protect the test area from contamination. Store it in darkness, when not in use.

6.2 Calibration of the non-fluorescent working standards

The non-fluorescent working standards shall be calibrated against ISO reference standards of level 3 in the instrument in which they are to be used.

Using the procedure appropriate to the instrument, calibrate the instrument with an IR3. Clean the working standards (see 6.4), measure the working standards and read off and record to the nearest 0,01 percentage point the radiance factors of the cleaned working standards.

NOTE In order to achieve agreement with the reference instrument, a working standard may be assigned multiple values, depending upon the working level and the purpose of the measurement. This applies if the working standard is translucent or glossy and if the linearity of the instrument scale is poor.

6.3 Use of non-fluorescent working standards

Use one plate as a primary working standard for checking and calibrating the instrument, and use the other much less frequently as a control plate for checking the primary working standard. The frequency with which the instrument needs to be calibrated depends on the type of instrument. Frequent calibration of the instrument tends to introduce undesirable fluctuations in the instrument, and the instrument should be recalibrated only when a check with the primary working standard indicates that calibration is necessary. Check the primary working standard periodically against the control plate. If any change in the radiance factor is noticed, clean the primary working standard by the procedure described in 6.4. If the change persists, clean and recalibrate both working standards against an appropriate IR3 reference standard.

The primary working standard should be checked against the control plate sufficiently often to ensure that any change in the primary working standard is discovered before an error is introduced into the calibration.

6.4 Cleaning the non-fluorescent working standards

Follow the manufacturer's instructions. In the case of working standards of opal glass or ceramic material, rinse with distilled water and detergent free from fluorescent ingredients while rubbing with a soft brush. Rinse thoroughly in distilled water and dry in the air in a dust-free environment without allowing anything to touch the surface. Leave it in a desiccator until it is optically stable.

7 Sampling

If the tests are being made to evaluate a lot, the sample should be selected in accordance with ISO 186. If the tests are made on another type of sample, make sure that the test pieces taken are representative of the sample received.

8 Preparation of the test pieces

Prepare the test pieces according to the instructions given in the relevant International Standard for the determination of radiance factors or optical properties based on the measurement of radiance factors.

If it is desired simply to measure the radiance factor, rather than some other optical property defined by another International Standard, follow the following procedure:

Avoiding watermarks, dirt and obvious defects, cut rectangular test pieces approximately 75 mm × 150 mm, taking care to avoid touching the future test area.

If it is desired to measure the intrinsic radiance factor, assemble test pieces in a pad with their top sides uppermost; the number should be such that doubling the number of test pieces does not alter the radiance factor. Protect the pad by placing an additional sheet on both the top and bottom of the pad; avoid contamination and unnecessary exposure to light or heat. Mark the top test piece in one corner to identify the sample and its top side.

NOTE If the top side can be distinguished from the wire side, it shall be uppermost; if not, as may be the case for papers manufactured on double wire machines, ensure that the same side of the sheet is uppermost throughout the pad.

If sufficient sheets are not available or if it is desired to measure a background-dependent radiance factor, select a suitable background and include a description of this background in the report.

9 Procedure

Determine the radiance factor as specified in the relevant International Standard for the determination of radiance factors or optical properties based on the measurement of radiance factors.

If it is desired simply to measure the radiance factor, rather than some other optical property defined by another International Standard, follow the following procedure.

9.1 Verification of calibration

Check the calibration of the instrument using a non-fluorescent working standard calibrated in relation to an IR3 (5.3). Recalibrate the instrument if necessary.

NOTE If the instrument is of the spectrophotometer type, and if the material to be measured contains or is suspected to contain a fluorescent component, the UV content of the illumination must be adjusted to match the desired illuminant using the fluorescent (5.2) and non-fluorescent (see 5.2) ISO level 3 standards in an iterative procedure according to the instrument maker's instructions. The procedure for UV-adjustment to match the CIE standard illuminant D65 is given in ISO 11475 and for UV-adjustment to match the CIE illuminant C in ISO 2470.

9.2 Measurement

Remove the protecting sheets from the test piece pad. Without touching the test area, use the procedure appropriate to the instrument, and the working standard, to measure the desired radiance factor. Read and record the value to the nearest 0,01 percentage points or better.

10 Calculation and expression of results

Express the radiance factor results with the number of decimals appropriate to the uncertainty and reproducibility of the procedure.

Calculate the results as required in the relevant International Standard for the determination of radiance factors or optical properties based on the measurement of radiance factors, e.g.:

ISO 2470, *Paper, board and pulps — Measurement of diffuse blue reflectance factor (ISO brightness)*

ISO 2471, *Paper and board — Determination of opacity (paper backing) — Diffuse reflectance method*

ISO 5631, *Paper and board — Determination of colour (C/2°) — Diffuse reflectance method*

ISO 9416, *Paper — Determination of light scattering and absorption coefficients (using Kubelka-Munk theory)*

ISO 11475, *Paper and board — Determination of CIE-whiteness, D65/10° (outdoor daylight)*

ISO 11476, *Paper and board — Determination of CIE-whiteness, C/2° (indoor illumination conditions)*

NOTE Some informative comments on the definition and calculation of the measurement uncertainty are given in Annex D.

11 Precision

Data relating to the precision of results obtained according to the procedure described in this International Standard are given in the relevant test method for the determination of radiance factors or optical properties based on the measurement of radiance factors. (See also Annex D).

12 Test report

Report the results as indicated in the relevant International Standard for the determination of radiance factors or optical properties based on the measurement of radiance factors.

If a radiance factor is determined according to the procedure described in this International Standard, the test report shall include the following details:

- a) date and place of testing;
- b) precise identification of the sample;
- c) a reference to this International Standard;
- d) the test results;
- e) the wavelength range, pitch and bandwidth if a spectrophotometer is used, or the type of filter if a filter instrument is used;
- f) the illuminant to which the UV-content of the illumination is adjusted if a spectrophotometer is used;

- g) the number of test pieces and the procedure adopted to calculate the reported results;
- h) the type of instrument used;
- i) any departure from this International Standard or any circumstances or influences that may have affected the results.

STANDARDSISO.COM : Click to view the full PDF of ISO 2469:2007

Annex A (normative)

Instruments for the measurement of radiance factor

The geometric, photometric and spectral characteristics of the instruments to which this International Standard applies are defined as follows:

A.1 Geometric characteristics

A.1.1 The test piece and reference area shall be subjected to diffuse illumination which is achieved by means of an integrating sphere (see Reference [2], 845.05.24) with an internal spectrally non-selective white diffusing surface and an internal diameter of (150 ± 3) mm.

A.1.2 The sphere shall be constructed as a dual-beam instrument so that a measurement can be made on a test piece, and a reference measurement can be made simultaneously on a reference region of the inner surface of the sphere.

A.1.3 The sphere shall be constructed or equipped with screens (baffles) to ensure that neither the test piece nor the reference region is directly illuminated by the light source.

A.1.4 The total area of the apertures and other non-reflecting areas in the sphere shall not exceed 13 % of the area of the inner surface of the sphere.

A.1.5 The receptor aperture shall be surrounded by a black annulus subtending a half-angle of $(15,8 \pm 0,8)^\circ$ at the centre of the test piece aperture. This black annulus serves as a "gloss trap" so that specularly reflected light from the test piece does not reach the receptor. The black annulus shall be matt and shall have a radiance factor of less than 4 %, at all wavelengths within the visible region.

A.1.6 The test piece aperture shall be designed so that the test piece itself is essentially a continuation of the internal wall of the sphere. The rim of the test piece aperture shall have a thickness of $(1,0 \pm 0,5)$ mm including the thickness of the internal coating.

A.1.7 The measured test area on the test piece shall be circular with a diameter of (28 ± 3) mm.

NOTE It is expected that the use of the smaller area will eliminate edge effects which can lead to a pseudo-non-linearity, and that this will lead to a higher reproducibility between instruments.

A.1.8 The diameter of the aperture shall be larger than that of the test area $(34,0 \pm 0,5)$ mm, to ensure that no light reflected from the rim of the test piece aperture or from the test piece within a distance of 1 mm from the rim of the aperture can reach the detector.

A.1.9 The test piece shall be viewed normally, i.e. at an angle of $(0 \pm 1)^\circ$ to the normal. Only reflected rays within a cone, the vertex of which is centred in the test piece aperture and the half-angle of which is not greater than 4° , shall fall on the receptor.

A.2 Photometric linearity

The photometric accuracy of the instrument shall be such that the residual departure from photometric linearity after calibration does not give rise to systematic errors exceeding 0,3 % radiance factor.

For the measurement of fluorescent papers, photometric linearity up to a total radiance factor value of at least 200 % is necessary in the wavelength region corresponding to the fluorescence emission.

A.3 Spectral characteristics

There are two main types of instrument which conform to this standard, known respectively as filter colorimeters and abridged spectrophotometers.

In the case of filter colorimeters, the spectral characteristics are determined by the filters inserted into the light beams in combination with the characteristics of the receptor, the sphere lining, the lamps and other optical parts of the instrument, or by a set of individual optical filters with different specific wavelengths. The filters shall be chosen so that the overall characteristics of the instrument agree with the spectral functions specified in the test methods relating to the determination of specific optical properties.

In the case of abridged spectrophotometers, the spectral characteristics are determined by the accuracy to which the individual receptors represent the nominal wavelengths assigned to them, the band-width associated with each receptor, and the values given to the mathematical functions used in the subsequent calculations. For colorimetry, the instrument shall incorporate not less than 16 receptors uniformly spaced over at least the range from 400 to 700 nm.

In instruments providing spectral data, the manufacturer shall indicate the optical bandpass of the instrument. Colorimetric data shall be computed only from spectral data presented at wavelength intervals equal to the instrument's optical bandpass-width. The centroid wavelength of each band shall not differ from its nominal wavelength by more than $\pm 0,5$ nm.

No procedure for calibration to eliminate errors in spectral characteristics is currently available. The spectral characteristics can be checked using suitable coloured reference standards. For specific purposes where close inter-instrument agreement is required, product-specific IR3 reference standards may be used to calibrate the instrument in relation to a reference instrument.

A.4 Computational procedures

To calculate tristimulus values as specified by the CIE illuminant and standard observer functions (1931 or 1964), the appropriate tables of weighting factors presented in ASTM E308-06 ¹⁾ for measurement at e.g. 10 nm or 20 nm intervals shall be used. The tristimulus values shall be calculated by direct summation using these tabulated values with no attempt at interpolation using e.g. a cubic spline function. The actual tables of values to be used are given in the relevant test methods for determining specific optical properties.

In ASTM E308-06 the tables to be used are those which assume that the spectral bandpass of the instrument used to obtain the data is equal to the measurement interval and is triangular in shape. These tables are to be used together with the data for which the manufacturer has identified the instrument bandpass as previously mentioned.

The instructions given in ASTM E308-06 shall be followed with regard to the summation of the tabulated values below 400 nm or above 700 nm if the measurement data do not cover the full extent of the tables.

If data from an instrument operating with a bandpass-width of 10 nm are to be presented and used at 20 nm intervals, the 10 nm data shall not be converted merely by taking the 10 nm data at 20 nm intervals. They should preferably be calculated using the equation

$$R_{20}(\lambda_i) = \frac{1}{4} R_{10}(\lambda_i - \Delta\lambda) + \frac{1}{2} R_{10}(\lambda_i) + \frac{1}{4} R_{10}(\lambda_i + \Delta\lambda) \quad (\text{A.1})$$

where

$$\Delta\lambda = 10 \text{ nm}$$

1) Reprinted, with permission, from E 308-06 Standard Practice for Computing the Colors of Objects by Using the CIE System, copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. A copy of the complete standard may be obtained from ASTM (www.astm.org).

It should be noted that such a computation may still be only approximate. This is presented as a guideline to the procedure which is preferred but it should not be interpreted as a recommendation within the scope of this International Standard.

A.5 UV-adjustment

For the measurement of materials containing fluorescent whitening agents, some means of setting the spectral power distribution of the radiation incident on the test piece to give a specified UV-content and of maintaining this setting or of mathematically simulating such a power distribution is required. For this purpose, a filter having a half-peak cut-off wavelength of 395 nm shall be used. If the filter is movable, it shall be mounted in a device which permits its position to be identified and maintained, and reproducibly reset.

A.6 Fluorescence elimination

For the measurement of radiance factors with the fluorescence effect eliminated, the instrument shall be equipped with a sharp cut-off UV-absorbing filter having a transmittance not exceeding 5 % at and below a wavelength of 410 nm and exceeding 50 % at a wavelength of 420 nm (i.e. a half-peak cut-off wavelength of 420 nm), or shall employ an equivalent procedure.

The cut-off filter shall have characteristics such that a reliable radiance factor value is obtained at 420 nm. This value shall be repeated at all lower wavelengths to provide adequate data for the colorimetric computations, provided that the International Standard for the quantity concerned does not include other instructions.

NOTE This procedure is equivalent to the ASTM E308-06 instruction to add the weighting functions if data for certain wavelengths is missing.

Instrument makers should recognize the need to provide the means to maintain at least three interchangeable and easily accessible calibrated situations, UV(D65) corresponding to the CIE standard illuminant D65, UV(C) corresponding to the CIE illuminant C, and UVex(420) corresponding to a fluorescence-eliminated (420 nm cut-off) situation.

Annex B (normative)

Calibration service — Photometric calibration

In this International Standard, a sequence of non-fluorescent reference standards of three different levels is mentioned, the ultimate reference standard (the ISO standard of level 1) being the “perfect reflecting diffuser”. The use of the perfect reflecting diffuser as ultimate reference is in full agreement with a recommendation made by the prime authority on optical properties, the Commission Internationale de l'Éclairage (CIE), in 1969.

To permit working instruments to relate their radiance factor measurements to this ultimate reference standard, the following procedure is specified.

B.1 Structure of the service

This calibration procedure involves two stages for fundamental reasons. The standardizing laboratory provides a transfer standard of level 2 with assigned radiance factor values directly *traceable to the perfect reflecting diffuser*. The authorized laboratory takes this transfer standard and, with the help of a reference instrument conforming to this International Standard, mediates to industrial laboratories a reference standard of level 3 with assigned radiance factor values which are traceable to the perfect reflecting diffuser *through an instrument having the prescribed geometric characteristics*. Calibration at the industrial laboratory level with a transfer standard of level 2 is not in accordance with this standard.

B.2 Standardizing laboratories

Certain laboratories equipped for absolute radiance factor measurements are appointed by ISO/TC 6 as “standardizing laboratories” in accordance with the provisions of ISO 4094. The standardizing laboratories issue ISO reference standards of level 2 (IR2) to the authorized laboratories.

The standardizing laboratories are required to exchange reference standards of level 2 at intervals of no longer than five years, so that the level of agreement between their measurements is monitored and maintained.

B.3 Authorized laboratories

Laboratories having the necessary technical competence and maintaining reference instruments having the characteristics specified in Annex A of this International Standard are appointed by ISO/TC 6 as “authorized laboratories” in accordance with the provisions of ISO 4094. Each authorized laboratory maintains an instrument conforming to the requirements of Annex A as a reference instrument which is calibrated using a reference standard of level 2. The authorized laboratories then issue ISO reference standards of level 3 (IR3) on request to industrial laboratories which use the IR3 for the purpose of calibrating their instruments and working standards periodically.

The authorized laboratories are required to exchange reference standards of level 3 at intervals of no longer than two years. It is expected that this procedure will achieve those accuracies which are suggested in the “Expression of results” clause in the International Standards dealing with the determination of specific optical characteristics.

B.4 IR3 Reference standards

The IR3 reference standards shall have the following properties:

- a) when properly cared for, their reflectance factors shall not change, within the accuracy of the instrument, over a reasonable period of time;
- b) they shall be clean, opaque, and uniform in reflectance factor;
- c) they shall be flat and shall have a smooth matte surface;
- d) they shall be free from fluorescence.

B.5 Assignment of calibration values to IR3s

For the calibration of abridged spectrophotometers, the authorized laboratory shall provide reference standards having assigned spectral data obtained by direct measurement of the IR3 in the calibrated reference instrument.

For the calibration of three-filter colorimeters, the authorized laboratory shall provide reference standards having assigned R_x , R_y and R_z values. These shall be calculated for C/2° illuminant/observer conditions as follows:

$$\begin{aligned} R_x &= (X - 0,167\,07\,Z)/78,321 \\ R_y &= Y/100 \\ R_z &= Z/118,232 \end{aligned} \tag{B.1}$$

where X , Y and Z are the tristimulus values, calculated according to A.4.

If a reference standard is required for the calibration of a three-filter colorimeter for measurement under D65/10° illuminant/observer conditions, the assigned $R_{x,10}$, $R_{y,10}$ and $R_{z,10}$ values shall be calculated as follows:

$$\begin{aligned} R_{x,10} &= (X_{10} - 0,167\,47\,Z_{10})/76,841 \\ R_{y,10} &= Y_{10}/100 \\ R_{z,10} &= Z_{10}/107,304 \end{aligned} \tag{B.2}$$

where X_{10} , Y_{10} and Z_{10} are the D65/10° tristimulus values, calculated according to A.4.

Annex C (normative)

Calibration service — UV-adjustment

For the measurement of fluorescent materials, special fluorescent reference standards are required to enable the relative UV-content in the illumination falling on the test piece to be adjusted to conform to the specified illuminant.

To enable this to be done, the following procedure is established.

C.1 Standardizing laboratories

A laboratory or laboratories equipped to make primary spectrofluorimetric measurements using the two-monochromator method is appointed by ISO/TC 6 as “standardizing laboratory” in accordance with the provisions of ISO 4094. This laboratory issues fluorescent ISO reference standards of level 2 (IR2) to the authorized laboratories. Such reference standards shall be assigned spectral total radiance factor data for the required illuminant.

C.2 Authorized laboratories

C.2.1 Laboratories having the necessary technical competence and maintaining reference instruments having the characteristics specified in Annex A of this International Standard are appointed by ISO/TC 6 as “authorized laboratories” in accordance with the provisions of ISO 4094.

NOTE It is anticipated that these authorized laboratories will be the same as those authorized in accordance with Annex B of this International Standard, but the standardizing laboratories will not necessarily be the same as those appointed according to Annex B since different equipment is required.

C.2.2 The authorized laboratory shall make any necessary adjustment to correct for differences in the basic photometric level between the instrument at the standardizing laboratory and the photometric level established at the authorized laboratory by the procedure described in Annex B, before calculating the appropriate property value for the IR2 and using this value to adjust the UV-content of the reference instrument. The calculations shall be carried out using 10 nm data and the weighting functions given in ASTM E308-06.

NOTE The property value required depends on the type of UV-adjustment being made, i.e. whether the adjustment is to conform to the CIE illuminant C or to the CIE illuminant D65. The exact details are given in the relevant International Standard.

C.2.3 The authorized laboratory shall take steps to ensure that directional effects in the IR2 which may affect the measurements at the standardizing laboratory are recognized and taken into account when determining the value to be used when transferring this calibration to an instrument providing diffuse illumination.

C.2.4 The authorized laboratories shall prepare ISO reference standards of level 3 (IR3) and shall supply these to industrial laboratories for the adjustment of the UV-level in their instruments.

C.2.5 The authorized laboratories are required to exchange reference standards of level 3 at intervals of no longer than two years, so that the level of agreement between their measurements is monitored and maintained.

C.3 IR3 fluorescent reference standards

C.3.1 The fluorescent reference standards shall consist of white paper uniform in radiance factor and aged for a sufficient time to give the paper an optical stability of 4-6 months without any deterioration greater than that permitted by the relevant International Standard.

C.3.2 The standards shall be prepared in the form of opaque pads and shall have a smooth non-glossy surface. The pad shall be covered with a suitable protective cover.

NOTE Fluorescent tablets and tiles are suitable local working standards but they have been shown not to be suitable for use as transfer standards for this procedure which is specific for white papers.

STANDARDSISO.COM : Click to view the full PDF of ISO 2469:2007