

# INTERNATIONAL STANDARD

ISO  
3633

First edition  
1991-06-15

---

---

## **Unplasticized poly(vinyl chloride) (PVC-U) pipes and fittings for soil and waste discharge (low and high temperature) systems inside buildings — Specifications**

*Tubes et raccords en poly(chlorure de vinyle) non plastifié (PVC-U) pour  
les systèmes d'évacuation d'eaux usées et d'eaux-vannes (à basse et à  
haute température) à l'intérieur des bâtiments — Spécifications*

STANDARDSISO.COM : Click to view the full PDF of ISO 3633:1991



Reference number  
ISO 3633:1991(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3633 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*.

Annexes A, B, C, D, E, F and G form an integral part of this International Standard. Annex H is for information only.

STANDARDSISO.COM : Click to view the full PDF of ISO 3633:1991

© ISO 1991

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Unplasticized poly(vinyl chloride) (PVC-U) pipes and fittings for soil and waste discharge (low and high temperature) systems inside buildings — Specifications

## 1 Scope

This International Standard lays down the specifications for unplasticized poly(vinyl chloride) (PVC-U) pipes and fittings, with nominal outside diameters of 16 mm to 400 mm, intended for domestic installations inside buildings for

- a) soil and waste discharge pipe lines (including the ventilation of these pipes), and
- b) internal rainwater pipes

for the transportation of domestic waste waters<sup>1)</sup> (low and high temperature).

**NOTE 1** For other uses of these pipes and fittings, reference should be made to the relevant section of ISO/TR 7024, to the manufacturer's instructions and to national regulations.

There are two types of pipes and fittings (type A and type B) for such discharge systems:

- type A, which shall be used only for primary and secondary ventilation pipework and internal rainwater applications;
- type B, which shall be used for soil and waste discharge systems and may also be used for any type A application.

This International Standard may also be applied to pipes, fittings and joints for discharges of industrial

origin, provided chemical and temperature resistance is taken into account.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 161-1:1978, *Thermoplastics pipes for the transport of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series*.

ISO 265-1:1988, *Pipes and fittings of plastics materials — Fittings for domestic and industrial waste pipes — Basic dimensions: Metric series — Part 1: Unplasticized poly(vinyl chloride) (PVC-U)*.

ISO 580:1990, *Injection-moulded unplasticized poly(vinyl chloride) (PVC-U) fittings — Oven test — Test method and basic specifications*.

ISO 1043-1:1987, *Plastics — Symbols — Part 1: Basic polymers and their special characteristics*.

ISO 2505:1981, *Unplasticized polyvinyl chloride (PVC) pipes — Longitudinal reversion — Test methods and specification*.

1) For the definition of the term "domestic waste waters" refer to annex A or, alternatively, to national regulations.

ISO 2507:1982, *Unplasticized polyvinyl chloride (PVC) pipes and fittings — Vicat softening temperature — Test method and specification*.

ISO 3127:1980, *Unplasticized polyvinyl chloride (PVC) pipes for the transport of fluids — Determination and specification of resistance to external blows*.

ISO 3606:1976, *Unplasticized polyvinyl chloride (PVC) pipes — Tolerances on outside diameters and wall thicknesses*.

ISO 4435:1991, *Unplasticized poly(vinyl chloride) (PVC-U) pipes and fittings for buried drainage and sewerage systems — Specifications*.

ISO/TR 7024:1985, *Above-ground drainage — Recommended practice and techniques for the installation of unplasticized polyvinyl chloride (PVC-U) sanitary pipework for above-ground systems inside buildings*.

ISO 8283-1:1991, *Plastics pipes and fittings — Dimensions of sockets and spigots for discharge systems inside buildings — Part 1: Unplasticized poly(vinyl chloride) (PVC-U) and chlorinated poly(vinyl chloride) (PVC-C)*.

### 3 Material

**3.1** The material shall consist substantially of poly(vinyl chloride) (PVC) to which may be added only those additives that are needed to facilitate the manufacture of pipes and fittings having good mechanical strength and opacity.

**3.2** The use of the manufacturer's own clean rework material from pipes and fittings made to this International Standard is permissible. No other rework material shall be used.

**3.3** Pipes and fittings shall be sufficiently stabilized against thermal ageing and ultraviolet (UV) light.

NOTE 2 Resistance to UV light is under study within ISO/TC 138.

### 4 Geometrical characteristics

#### 4.1 Pipe dimensions

Pipe dimensions shall be in accordance with ISO 161-1 and ISO 3606.

#### 4.1.1 Nominal outside diameter and wall thickness

Nominal outside diameters and wall thicknesses are classified into two size ranges: a primary size range (see table 1 and table 2) and a secondary size range (see table 3 and table 4). If dimensions other than those given for the primary size range are necessary, they shall be selected from the secondary size range.

##### 4.1.1.1 Primary size range

**Table 1 — Nominal outside diameter — Primary size range**

Dimensions in millimetres

40	50	75	90	110	125	160
----	----	----	----	-----	-----	-----

**Table 2 — Wall thickness — Primary size range**

Dimensions in millimetres

Nominal outside diameter <i>D</i>	Minimum wall thickness $t_{\min}$	
	Type A	Type B
40	1,8	3,2
50	1,8	3,2
75	1,8	3,2
90	1,9	3,2
110	2,2	3,2
125	2,5	3,2
160 <sup>1)</sup>	3,2 <sup>1)</sup>	4

1) May also be suitable for type B applications, provided that the functional test requirements are fulfilled.

##### 4.1.1.2 Secondary size range

**Table 3 — Nominal outside diameter — Secondary size range**

Dimensions in millimetres

16	20	25	32	63	200	250	315	400
----	----	----	----	----	-----	-----	-----	-----

**Table 4 — Wall thickness — Secondary size range**  
Dimensions in millimetres

Nominal outside diameter <i>D</i>	Minimum wall thickness <i>e</i> <sub>min</sub>	
	Type A	Type B
16	—	1,8
20	—	2,3
25	—	3,2
32	1,8	3,2
63	1,8	3,2
200	3,9	4,9
250	4,9	6,2
315	6,2	7,7
400	7,8	9,8

#### 4.1.2 Length of pipe

The nominal length of a pipe shall be measured as shown in figure 1. For pipes with sockets, the nominal length is considered to be the distance between the ends minus the socket depth. For practical reasons, this length is measured to the outside of the socket.

### 4.2 Dimensions of fittings

#### 4.2.1 Basic dimensions

Basic dimensions of fittings shall be given by the manufacturer, and the dimensions shall be defined as in ISO 265-1.

#### 4.2.2 Wall thickness

The wall thickness shall be at least equal to the minimum wall thickness of the pipe of the same size unless otherwise specified in 4.3.2.

### 4.3 Socket and spigot dimensions of pipes and fittings

#### 4.3.1 Basic dimensions

Basic dimensions of sockets and spigots shall be as given in ISO 8283-1 for nominal diameters up to 200 mm and as given in ISO 4435 for nominal diameters greater than 200 mm.

#### 4.3.2 Wall thickness of sockets on pipes and fittings

The minimum wall thickness of sockets for joints of the primary size range shall meet the requirements of table 5 (see figure 2 for an example).

**Table 5 — Minimum wall thickness of sockets on pipes and fittings — Primary size range**  
Dimensions in millimetres

Nominal outside diameter <i>D</i>	<i>e</i> <sub>2</sub> min.		<i>e</i> <sub>3</sub> min.	
	Type A	Type B	Type A	Type B
40	1,6	2,9	1	2,4
50	1,6	2,9	1	2,4
75	1,6	2,9	1	2,4
90	1,7	2,9	1,1	2,4
110	2	2,9	1,2	2,4
125	2,3	2,9	1,4	2,4
160	2,9	3,6	1,8	3

When a seal ring is firmly retained by means of a seal ring retaining component (see figure 3 for an example), the wall thickness of the socket in this area and that of the seal ring retaining component may be added together to achieve the required *e*<sub>3</sub> dimension provided that they are not separated by the seal ring.

The minimum values of *e*<sub>3</sub> given in table 5 apply only to those parts of the ring seal zone where the liquid in the pipe comes into contact with the fitting. For those parts of the fitting that do not come into contact with the liquid, i.e. beyond the designated seal point, thinner walls are permitted.

Seal ring retaining components may be manufactured in plastics other than PVC-U.

In all cases, the components shall meet the functional test requirements specified in clause 7.

## 5 Mechanical test requirements

### 5.1 Pipes

Either the impact test or the tensile test as specified in 5.1.1 or 5.1.2 may be selected to satisfy the test requirements.

#### 5.1.1 Impact strength (alternative to 5.1.2)

The true impact rate (TIR) shall not exceed 10 % at 20 °C when tested in accordance with ISO 3127.

#### 5.1.2 Tensile strength (alternative to 5.1.1)

When determined in accordance with a method agreed on between the interested parties, the maximum tensile strength plotted during the test shall not be less than 45 MPa and the elongation at break shall not be less than 80 %.




Figure 1 — Nominal pipe length and definitions




Figure 2 — Socket details




Figure 3 — Example of a seal retaining cap

## 5.2 Fittings — Impact strength

Five fittings of each diameter and type shall be conditioned for at least 30 min at a temperature of 0 °C ± 1 °C. Within 10 s after the conditioning treatment, each fitting shall be dropped freely in various positions on to a flat concrete floor from the heights specified below:

- for  $D \leq 75$  mm, drop from  $(2 \pm 0.1)$  m;
- for  $D > 75$  mm, drop from  $(1 \pm 0.1)$  m.

If none of the specimens is damaged in the test, the fittings shall be accepted. If one fitting is damaged, the test shall be repeated with five further fittings. None of these last five fittings shall be damaged.

### NOTES

3 This is an optional test, to be carried out only if required in a national standard, but is mandatory for fittings with sealing caps or rings and for fittings fabricated from pipes.

4 In the context of this test, "damage" means any visible split or any complete breakage in the body of the fitting. Surface scratches, scuffing, or chipping of edges which may occur in the test does not constitute damage.

## 6 Physical test requirements

### 6.1 Pipes

#### 6.1.1 Vicat softening temperature

The Vicat softening temperature shall be not less than 79 °C when determined in accordance with ISO 2507.

#### 6.1.2 Longitudinal reversion

The longitudinal reversion shall not exceed 5 % when determined in accordance with ISO 2505.

## 6.2 Fittings

### 6.2.1 Vicat softening temperature

The Vicat softening temperature shall be not less than 77 °C when determined in accordance with ISO 2507.

### 6.2.2 Oven test

Moulded fittings shall meet the requirements of ISO 580.

## 7 Functional test requirements (type tests)

### 7.1 Watertightness

Joints between pipes and fittings, pipes and pipes, and fittings and fittings shall not leak when tested in accordance with annex B.

### 7.2 Airtightness

Joints between pipes and fittings, pipes and pipes, and fittings and fittings shall remain airtight when tested in accordance with annex C.

### 7.3 Elevated-temperature cycling test

The test assembly used shall meet the requirements given in either annex D or annex E. Where national standards specify which of these two tests is to be used, they shall be complied with.

Only type B pipes and fittings are required to satisfy these requirements.

Annex F specifies the information to be provided and the symbols to be used in the test report.

#### 7.4 Axial shrinkage

The axial shrinkage shall not exceed 2 % when determined in accordance with annex G.

NOTE 5 This is an optional test to be carried out only if required by a national standard.

#### 8 Elastomeric sealing elements and adhesives

All elastomeric sealing elements and adhesives shall be as specified by the manufacturer of the fittings.

The sealing elements and adhesives shall not have a detrimental effect on the pipes or fittings, i.e. they shall not cause the test assembly to fail the functional tests.

#### 9 Delivery conditions

The internal and external surfaces of pipes and fittings shall be smooth and free from grooving, blistering and any other surface defect. The materials shall not contain visible impurities or pores. Pipe ends shall be cleanly cut, and the ends of pipes and fittings shall be square with the axis of the pipe.

### 10 Marking

Pipes, fittings and sealing rings shall be marked clearly and indelibly so that legibility is maintained for the life of the products under normal conditions of storage, weather and use.

The markings may be integral with the product or on a label. The markings shall not damage the product.

#### 10.1 Pipes

Pipes shall be marked with at least the following information:

- manufacturer's name or trade mark;
- pipe material;
- nominal diameter of pipe;
- nominal wall thickness of pipe;

- manufacturing information, in plain text or in code, providing traceability of the production period to within the year and month and the production site if the manufacturer is producing at several national or international sites;

- the number of this International Standard.

Pipes with a nominal laying length up to and including  $z_2$  metres shall be marked at least once. Pipes with a nominal laying length greater than  $z_2$  shall be marked at intervals of  $z_3$  metres at the most. The values of  $z_2$  and  $z_3$  shall be as specified by the authorities in each country.

#### 10.2 Fittings

Fittings shall be marked with at least the following information:

- manufacturer's name or trade mark;
- fitting material (may be given on packing only in the case of PVC, provided this information is not required on each article by national authorities);
- nominal diameter of fitting;
- classification (where applicable);
- values of angles, if any;
- manufacturing information, in plain text or in code, providing traceability of the production period to within the year and month and the production site if the manufacturer is producing at several national or international sites (may be given on packing only, provided this information is not required on each article by national authorities);
- the number of this International Standard (may be given on packing only, provided this information is not required on each article by national authorities).

#### 10.3 Sealing rings

Sealing rings shall be marked with at least the following information:

- manufacturer's name or trade mark;

- nominal dimension of ring;
- manufacturing information, in plain text or in code, providing traceability of the production period to within the year and the production site if manufacturer is producing at several national or international sites.

No markings are required on sealing rings which are moulded to pipes or fittings or any other marked component.

#### **10.4 Designation of the material (in accordance with ISO 1043-1)**

PVC-U

STANDARDSISO.COM : Click to view the full PDF of ISO 3633:1991

## Annex A (normative)

### Definition of domestic waste waters

**domestic waste waters:** Waters discharged and diverted into the sewage system, in particular

a) waters that have become altered in composition and have become fouled (or impure) by being used domestically (including waters from flushing systems containing human excrement and, if necessary or authorized, animal excrement, and

waters from normal households, offices, old people's homes, hotels, schools, etc.), and

b) rainwater, if a separate discharge channel is not available.

Such waters never have a temperature exceeding 100 °C continuously for more than 2 min and have a pH value normally in the range pH 2 to pH 12.

## Annex B (normative)

### Watertightness test

#### B.1 Apparatus

**B.1.1 Apparatus**, to which the test assembly can be connected, allowing a controlled water pressure to be applied.

**B.1.2 Precision pressure gauge.**

#### B.2 Test assembly

Pipes, fittings and joints in accordance with this International Standard in all other respects shall be used.

The connection (joint) shall be made in accordance with the manufacturer's instructions.

#### B.3 Procedure

If the joint to be tested permits deflection, perform the test with the test assembly under the maximum possible deflection of the axis without forcing.

Connect the test assembly (see clause B.2) to the precision pressure gauge (B.1.2). By allowing water to enter the test assembly, gradually increase the internal pressure from 0 MPa to 0,05 MPa (0 bar to 0,5 bar) over a period of not greater than 15 min and maintain the pressure of 0,05 MPa (0,5 bar) for at least 15 min.

#### B.4 Test requirements

The test requirement (see 7.1) shall be fulfilled for all types of test assembly, including those combining minimum spigot ends and maximum sockets.

## Annex C

(normative)

### Airtightness test

#### C.1 Apparatus

**C.1.1 Apparatus**, to which the test assembly can be connected, allowing a controlled air pressure to be applied.

A suitable apparatus is shown in figure C.1.

#### C.1.2 Precision pressure gauge or manometer.

#### C.2 Test assembly

Pipes, fittings and joints in accordance with this International Standard in all other respects shall be used.

The connection (joint) shall be made in accordance with the manufacturer's instructions.

The test assembly shall consist of a specimen of pipe mounted in two clamped blocks. Seal one end of the pipe with a plug that has a combined water and air inlet. Insert any fitting or joint into the open end of the pipe. The joint or fitting shall then be sealed at all open ends with plugs, one of which has a water outlet and shut-off valve mounted centrally in the sealing plug.

#### C.3 Procedure

**C.3.1** Apply a strong solution of soapy water or detergent around the annular space between the mouth of the fitting and the pipe.

**C.3.2** Open the water outlet valve and close the air inlet valve on the pipe shut-off.

**C.3.3** Open the water inlet valve. When the assembly is half full, that is say when water flows from the outlet, close the water inlet and outlet valves.

**C.3.4** Open the air inlet valve and increase the internal air pressure to  $0,01 \text{ MPa} \pm 0,001 \text{ MPa}$  ( $0,1 \text{ bar} \pm 0,01 \text{ bar}$ ) at ambient temperature. Maintain this pressure for 5 min.

**C.3.5** Note, during this 5 min period, any leaks which occur between the mouth of the fitting and the pipe, and which are evident by the formation of bubbles.

**C.3.6** Deflect the pipe manually in the socket of the fitting until it reaches the maximum permissible deflection for the particular joint under test. Carry out this deflection at  $0^\circ$ ,  $90^\circ$ ,  $180^\circ$  and  $270^\circ$  (see figure C.1), maintaining it for 1 min in each of these directions.

#### C.4 Test requirements

No water leaks shall occur, but if bubbles appear at any time during the test, a new application of soapy water or detergent shall be made. If there is still a continuous emission of bubbles during the test, the joint shall be deemed not to meet the requirements of the test.

The test requirements shall be fulfilled for all types of test assembly, including those combining minimum spigot ends and maximum sockets.




Figure C.1 — Test assembly for airtightness test

## Annex D

(normative)

### Elevated-temperature cycling test — 1 500-cycle test (type B pipes and fittings — Primary size range)

#### **D.1 Test assembly**

The test assembly shall consist of a vertical stack of pipes with fittings and two near-horizontal pipe assemblies with fittings in accordance with figure D.1. Installation shall be carried out on a firm wall or frame with guide and anchor brackets, with no other support of the test assembly.

Anchor brackets shall be located directly below or behind the sockets of each pipe length. Guide brackets shall be placed not less than  $10D$  apart for near-horizontal assemblies. (An exception to this is the first pipe in the near-horizontal line from the inlet, where possible sagging is to be measured.)

Room for expansion of pipes shall be provided for all spigot ends of pipes, but not for the spigot ends of fittings. The entry of hot water into the test assembly shall be direct; there shall be no heat-absorbing intermediate pieces.

#### **D.2 Procedure**

**D.2.1** Carry out a watertightness test on the test assembly under the conditions described in E.3.1.

**D.2.2** Subject the test assembly to the passage of hot and cold water according to the following schedule for 1 500 cycles:

- a) 30 l of water at a temperature of  $93\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  (measured at the point of entry) over a period of 1 min (30 l/min);
- b) rest and drain period of 1 min;
- c) 30 l of water at a temperature of  $15\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$  (measured at the point of entry) over a period of 1 min (30 l/min);
- d) rest and drain period of 1 min.


#### **D.3 Test requirements**

**D.3.1** On completion of the test, fill the test assembly with water, at a temperature not exceeding  $20\text{ }^{\circ}\text{C}$ , to a head of 0,5 m. Leave for a minimum period of 15 min and then visually check for leaks. Any leakage shall be deemed a failure of the test assembly.

**D.3.2** Check for sagging between guide brackets at a distance of  $5D$  from any individual bracket. Any sagging greater than  $0,1D$  shall be deemed a failure.

#### **D.4 General information**

See annex F.



NOTE – The fittings shall be assembled without undue stresses. The test assembly illustrated is only representative and the positions of the joints are not mandatory but should follow appropriate installation techniques (see ISO/TR 7024) and the manufacturer's instructions.

Figure D.1 – Test assembly for elevated-temperature cycling test (1500 cycles)

## Annex E

(normative)

### Elevated-temperature cycling test — 5-cycle test

#### E.1 Test assembly

The test assembly shall consist of a vertical stack of pipes with fittings and two near-horizontal pipe assemblies with fittings in accordance with figure E.1. Installation shall be carried out on a firm wall or frame with guide and anchor brackets, with no other support of the test assembly.

Anchor brackets shall be located directly below or behind the sockets of each pipe length. Guide brackets for near-horizontal assemblies shall be positioned as shown in figure E.1.

It shall be checked that the test assembly exhibits no sagging greater than  $0,1D$  at the mid-point between two guide brackets (see figure E.1).

Devices shall be provided, and positioned as indicated in figure E.1, to measure any sagging  $f_1$  and  $f_2$  of the test assembly.

Room for expansion of pipes shall be provided for all spigot ends of pipes, but not for the spigot ends of fittings. The entry of hot water into the test assembly shall be direct; there shall be no heat-absorbing intermediate pieces.

#### E.2 Procedure

**E.2.1** Test the assembly for watertightness and airtightness in accordance with E.3.1 and E.3.2.

**E.2.2** Subject the assembly to the passage of hot and cold water according to the following schedule for 5 cycles:

- a) circulation of water at  $93\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$  for 15 min, at a flow-rate of 0,3 l/s (18 l/min);
- b) circulation of water at  $15\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$  for 10 min, at a flow-rate of 0,3 l/s (18 l/min).

During the cycling test

- a) check that the temperature of the water remains constant within the specified limits;
- b) note any leaks from the test assembly and any "incidents" which may have an influence on the results;

- c) record the sagging  $f_1$  and  $f_2$  between guide brackets.

**E.2.3** After completion of the cycling test, carry out the watertightness test again, as described in E.3.1.

#### E.3 Tightness test procedures

##### E.3.1 Watertightness

Carry out the following procedure.

- a) Seal off the lower end of the test assembly.
- b) Apply a pressure of at least 0,01 MPa (0,1 bar) to each joint by filling the installation with water.
- c) Maintain the pressure for a period of 1 min.
- d) Take note of any leaks at each joint.

##### E.3.2 Airtightness

Carry out the following procedure.

- a) Seal off the ends of the test assembly.
- b) Coat the annular space between spigot and socket ends of joints with soapy water.
- c) Apply an air pressure of 0,01 MPa (0,1 bar) at ambient temperature.
- d) Maintain the pressure for a period of 1 min.
- e) Take note of any leaks, evident through the formation of bubbles.

#### E.4 Test requirements

**E.4.1** The joints shall remain watertight and airtight before and after the 5-cycle test.

**E.4.2** The sagging at the mid-point between two guide brackets shall not exceed  $0,1D$ .

#### E.5 General information

See annex F.




Figure E.1 — Test assembly for elevated-temperature cycling test (5 cycles)