

NFPA No.

651

ASA Z12.11



DUST EXPLOSION PREVENTION

ALUMINUM POWDER 1963

An American Standard

**CHARLES S. MORGAN LIBRARY
NATIONAL FIRE PROTECTION ASSOCIATION
1 BATTERYMARCH PARK
QUINCY, MA 02269-9101**



Fifty Cents

Copyright © 1963

NATIONAL FIRE PROTECTION ASSOCIATION

International

60 Batterymarch Street, Boston 10, Mass.

3M-6-63-FP

Printed in U.S.A.

National Fire Protection Association

International

The National Fire Protection Association was organized in 1896 to promote the science and improve the methods of fire protection. Its membership includes national and regional societies and associations (list on outside back cover) and twenty-one thousand individuals, corporations, and organizations. Anyone interested may become an Associate Member; the annual dues are \$20.00. Full membership information is available on request.

This is one of a large number of publications on fire safety issued by the Association. All NFPA standards and recommended practices, including this text, are prepared by the technical committees of the NFPA and adopted at an Annual Meeting of the Association. They are intended to prescribe reasonable measures for minimizing losses of life and property by fire.

This text and most other NFPA standards and recommended practices are published in the **National Fire Codes**, a compilation of NFPA's official technical material. Full information on the availability of these Codes and other NFPA publications can be secured from the Association.

Official NFPA Definitions

SHALL is intended to indicate requirements.

SHOULD is intended to indicate recommendations, or that which is advised but not required.

APPROVED refers to approval by the authority having jurisdiction.

Units of measurements used here are U. S. standard. 1 U. S. gallon = 0.83 Imperial gallons = 3.785 liters. One foot = 0.3048 meters. One inch = 25.40 millimeters. One pound per square inch = 0.06805 atmospheres = 2.307 feet of water.

Approved Equipment

The National Fire Protection Association does not "approve" individual items of fire protection equipment, materials or services. The suitability of devices and materials for installation under NFPA standards is indicated by the listing of nationally recognized testing laboratories, whose findings are customarily used as a guide to approval by agencies applying these standards. Underwriters' Laboratories, Inc., Underwriters' Laboratories of Canada, the Factory Mutual Laboratories and the American Gas Association (gas equipment) test devices and materials for use in accordance with the appropriate standards, and publish lists which are available on request.

Copyright and Republishing Rights

This publication is copyright © by the National Fire Protection Association. Permission is granted to republish material herein in laws or ordinances, and in regulations, administrative orders or similar documents issued by public authorities. Those desiring permission for other republication should consult the National Fire Protection Association.

Discount Prices on this Pamphlet

The following schedule of discount prices for multiple copies of this pamphlet have been established:

6-11 copies: 10%	24- 47: 20%
12-23 copies: 15%	48-100: 25%
Over 100: Special Quotation	

Code for the Prevention of Dust Explosions in the Manufacture of Aluminum Powder

NFPA No. 651 — 1963

ASA Z12.11 — 1963 UDC 628.511:83/.84

1963 Edition of No. 651

The 1963 edition of the Code for the Prevention of Dust Explosions in the Manufacture of Aluminum Powder incorporates changes prepared by the Sectional Committee on Metal Dusts and adopted at the 1963 Annual Meeting of the National Fire Protection Association on recommendation of the Committee on Dust Explosion Hazards. It supersedes the 1959 edition. Amendments in 1963 consisted of change of "aluminum bronze powder" to "aluminum powder" in the title and wherever else these words appeared. This edition was approved as an American Standard by the American Standards Association on June 27, 1963.

Origin and Development of No. 651

This Code was originally prepared by the Committee on Dust Explosion Hazards in 1938 and 1939. It was first adopted in 1939 and revised in 1946, 1952, 1959, and 1963.

Sectional Committee on Metal Dusts

R. W. Andrews, Jr., *Chairman*

D. P. Congdon
E. W. Cousins
Robert F. Dilly
Wm. G. Griffin
G. C. Koth
(alternate to E. W. Cousins)

Don O. Noel
John P. O'Neill
(alternate to Wm. G. Griffin)
Thomas A. Oravec
J. A. Peloubet

NFPA Committee on Dust Explosion Hazards

C. G. Gibson, *Chairman*,

Ontario Department of Labour, 8 York St., Toronto 1, Ont., Canada
(rep. Canadian Assn. of Administrators of Labour Legislation)

R. W. Andrews, Jr., American Society of Mechanical Engineers

Dr. Marlon Barnes, The Sulphur Institute

C. M. Blaesi, NFPA Committee on Blower Systems

Dean M. Clark, Grain Elevator and Processing Superintendents

D. P. Congdon, Factory Insurance Assn.

E. W. Cousins, Factory Mutual Engineering Division

M. F. Crass, Jr., Manufacturing Chemists' Assn., Inc.

Robert F. Dilly, National Board of Fire Underwriters

R. E. Dufour, Underwriters' Laboratories, Inc.

Fred G. Ely, The American Boiler and Affiliated Industries

C. W. Gordon, Mgr., Combustion Engineering, Inc. (Personal)

William G. Griffin, U. S. Department of Labor

Douglas L. Hail, Millers' National Federation

Warren Hallen, West Coast Lumbermens Assn.

S. B. Hansen, American Foundrymen's Assn.

S. F. Henderson, National Electrical Manufacturers Assn.

Guy Isenberg, Manufacturing Chemists' Assn., Inc.

George L. Kitchen, Terminal Elevator Grain Merchants Assn.

H. C. Lee, Assn. of Mill & Elevator Mutual Ins. Cos.

Dr. E. G. Meiter, American Industrial Hygiene Assn.

John Nagy, U. S. Bureau of Mines

Don O. Noel, Pres., Metal Powder Producers Assn. of the Metal Powder Industries Federation

Thomas A. Oravec, International Assn. of Governmental Labor Officials

J. A. Peloubet, The Magnesium Assn.

J. M. Robinson, Assn. of Casualty & Surety Cos.

W. H. Russell, Assn. of Casualty & Surety Cos.

Arthur C. Schrier, National Confectioners' Assn.

Lincoln D. Scott, Corn Industries Research Foundation

E. J. Sestak, Factory Insurance Assn.

T. T. Singer, Western Actuarial Bureau

Lester C. Smith, The Spencer Turbine Co. (Personal)

George H. Steel, American Society of Safety Engineers

D. C. Sullivan, Underwriters Grain Assn.

J. K. Sundermeyer, Society of the Plastics Industry, Inc.

Paul J. Turner, Great Northern Railway (Personal)

H. L. Walker, Edison Electric Institute

Alternates.

L. H. Gretzer, American Society of Safety Engineers. (Alternate to George H. Steel.)

John F. Hennessey, National Confectioners' Assn. (Alternate to Arthur C. Schrier.)

J. M. Jensen, Corn Industries Research Foundation. (Alternate to Lincoln D. Scott.)

Frank Jun, Millers' National Federation. (Alternate to Douglas L. Hail.)

G. C. Koth, Factory Mutual Engineering Division. (Alternate to E. W. Cousins.)

Gordon A. Olson, Edison Electric Institute. (Alternate to H. L. Walker.)

John P. O'Neill, U. S. Department of Labor. (Alternate to Wm. G. Griffin.)

G. D. Perkins, Association of Mill & Elevator Mutual Insurance Cos. (Alternate to H. C. Lee.)

A. J. Stabb, Underwriters' Laboratories, Inc. (Alternate to R. E. Dufour.)

James B. Walker, The American Boiler and Affiliated Industries. (Alternate to Fred G. Ely.)

Contents

1. Introduction	651- 4
2. Location and Buildings of Aluminum Powder- making Plant	651- 5
3. Making and Conveying of Powder	651- 7
4. Electricity for Light and Power	651- 8
5. Control of Static Electricity	651- 9
6. Prevention of Accumulation of Aluminum Powder or Dust	651- 9
7. Prevention of Ignition of Aluminum Powder . . .	651-10
8. Aluminum Powder Storage	651-12
9. Fire Fighting Methods for Prevention of Aluminum Powder Explosions	651-13
10. Safety Provisions	651-14

**Code for the Prevention of Dust Explosions
in the Manufacture of
Aluminum Powder**

NFPA No. 651 — 1963

Chapter 1. Introduction.

11. The objective of this Code is to reduce the hazards of ignition and explosions in the manufacture of aluminum flake powder and atomized aluminum granular particles and/or the dust of any aluminum alloy that is explosive in an environmental gas, as determined by test.

12. Where the code has reference to plant location or construction, or the installation of radically new types of equipment, the specifications are not retroactive in application.

13. All new installations should be under the supervision of engineers qualified by experience in the design, construction and operation of equipment for the purpose.

14. This code is not intended to apply to situations where waste dust is produced by operations such as grinding, buffing and polishing of aluminum castings. Prevention of fires and explosions in industries where aluminum and aluminum alloys are subject to processing or finishing operations in which a fine metallic dust or powder is liberated is covered in NFPA No. 65, the Code for the Processing and Finishing of Aluminum.

15. DEFINITIONS. In this code the following words are used as defined below:

“Shall” is intended to indicate requirements.

“Should” is intended to indicate recommendations, or that which is advised but not required.

“Approved” refers to approval by the authority having jurisdiction in the enforcement of standards.

Chapter 2. Location and Buildings of Aluminum Powder-making Plant.

21. LOCATION OF THE PLANT: The plant should be located on a tract of land large enough so that the buildings in which the powder is manufactured shall be at least 300 feet distant from occupied structures such as public buildings, dwellings, stores or manufacturing establishments other than those which are a part of the powder manufacturers' plant. The premises in which are located the powder-making buildings should be surrounded by high strong fencing with suitable entrance gates under charge of a guard to the property.

22. DIFFERENT OPERATIONS IN THE MANUFACTURE of aluminum powder should be located in separate buildings further subdivided into as many small units as practicable, by substantial brick or reinforced concrete division walls without openings. Separate buildings (other than the small units of a major process section) should preferably be separated by not less than 50 feet of space and in no case should they be less than 25 feet apart, unless barricades, similar to those used in explosives manufacturing plants, are built between the buildings. Where two buildings are less than 50 feet apart, only one of those shall have windows or doors in the wall facing the other building.

23. ELECTRIC OR STEAM POWER GENERATORS shall be in a separate building or buildings which should be at least 100 feet from the dust-making buildings.

24. BUILDING CONSTRUCTION: All buildings used for the manufacture, packing or loading for shipment of aluminum powder shall conform with the following requirements:

a. **CHARACTER OF BUILDINGS:** They shall be of one-story type, with no basements, and constructed of noncombustible materials throughout, and the buildings shall be designed so that every internal surface is readily accessible to facilitate cleaning. In all building walls of rooms where dust may be produced, which are not of monolithic construction, all masonry joints shall be thoroughly slushed with mortar and troweled smooth so as to leave no interior or exterior voids for the infiltration and accumulation of aluminum powder.

b. **CONSTRUCTION WITH REFERENCE TO POSITION OF BUILDINGS:** Where two buildings face each other at a distance of less than 50 feet, one of the facing walls shall be of reinforced concrete or brick construction without openings; the other facing wall may be of "daylight type" construction.

c. **COMMUNICATIONS BETWEEN BUILDINGS:** Buildings separated by not less than 50 feet of space (or small units of one major process section) may communicate through enclosed passageways of noncombustible construction; provided, that such enclosed passageways are specially designed for the release of internal pressures and all openings to such passageways are protected by self-closing fire doors approved for the protection of openings in fire division walls.

d. **FRAMES OF DOORS AND WINDOWS** should be of metal; the doors shall be approved self-closing fire doors. There should be adequate window areas both for light and in case of an explosion to afford relief of pressure on rupturing; windows which may be opened, should be hinged at the top, open outward and if fastened with catches, these should release on moderate pressure from the inside. Each room should have at least two widely separated exits to corridors or to the outside.

e. **FLOORS OF BUILDINGS** in which there are dust-making operations should be of concrete, covered with non-sparking composition which provides a hard, smooth surface.

f. **ROOFS OF BUILDINGS** in which there are dust-making operations shall be supported on girders so designed as to minimize the area of surfaces on which dust may collect. Where these surfaces are unavoidably present, and on other more or less horizontal places, such as wide girder flanges and window ledges, they shall be covered by a steeply sloping plaster filling. The roof covering shall be as light as practicable, but fire resistant and so arranged that it will be easily blown off by an internal explosion. Any sheet metal used in the roof covering shall be well cemented to prevent leakage and be well painted with aluminum paint, or else galvanized and well maintained to prevent corrosion, which might cause leakage.

g. **GROUNDING AND LIGHTNING PROTECTION:** All steel work should be well grounded to a suitable ground outside the building, in accordance with NFPA No. 78, the Code for Protection Against Lightning. Lightning rods should be provided for all boiler house stacks or chimneys and high points on buildings. The power lines should be adequately protected against lightning. A lightning arrester system should be provided around or within the building area, of such a capacity as to fully protect all buildings in that area from lightning.

Chapter 3. Making and Conveying Powder.

31. CONSTRUCTION AND GROUNDING OF DUST-MAKING MACHINES: All dust-making machines and conveyors shall be so constructed as to minimize the escape of dust into the rooms in which they are located. All parts of the machinery and conveyors shall be thoroughly grounded to prevent static sparks (see Chapter 5, Control of Static Electricity).

32. CONVEYING OF ALUMINUM POWDER: When this is done pneumatically it shall be in non-ferrous conveyor ducts; if transported in movable containers these shall be constructed throughout of non-ferrous, non-sparking material with a non-ferrous metal lining and provided with wheels or casters with non-sparking tires. When these containers have to be transported in the open, they shall be protected from the weather by covers. Pneumatic conveying is a common method of transferring the dust from place to place in a building or to an adjacent building. Preferably an inert gas mixture should be used instead of air in such a system, wherever the concentration of powder is within the explosive range, or likely to become so.

a. **PREVENTION OF CONDENSATION AND DRYING IN CONVEYOR DUCTS:** Provision should be made, in both the design and installation of conveyor ducts, to guard against possible condensation of moisture within the ducts, and to provide means so that it may be completely and thoroughly dried out after any period of idleness, before it is again put into service. Such drying operation should always be thoroughly carried out, preferably by the use of warm dry air, for several hours before resuming operations. All conveyor ducts, where practicable, should have a definite inclination from the horizontal to facilitate cleaning and draining.

33. RELIEF VENTS OF CONVEYOR DUCTS: Wherever, in the ducts, it is practicable to have relief vents of sufficient area extending to the outside of the building, these shall be provided.

a. **WORKING PRESSURE STRENGTH OF DUCTS:** Wherever damage may result from the rupture of a duct, in case the relief vent does not offer sufficient relief, the duct should be designed for a working pressure of at least 100 pounds per square inch. Where so located that no damage will result from its bursting, it should be of the lightest construction possible.

34. FAN CONSTRUCTION AND ARRANGEMENTS: Blades and housing of fans that are used to actuate movement of the air or inert gas in conveying ducts should be constructed of non-sparking material such as bronze or aluminum. The arrangements should be such that intercepting screen-cloth filters suitably grounded, or the design of the ducts, will prevent aluminum dust from passing into the fan; in all cases, however, it is advisable that the fan blades or propellers should be made of non-sparking material. Wherever possible, any fans into which dust may enter should be placed outside of the dust-making building. This arrangement should be particularly followed in dealing with the finest particle size of aluminum powder or any aluminum-alloy dust that is explosive in air.

Chapter 4. Electricity for Light and Power.

41. ELECTRICAL WIRING AND EQUIPMENT. All electrical wiring and equipment in Class II locations, as defined in Article 500 of NFPA No. 70, the National Electrical Code, shall be installed in accordance with the requirements of Article 502 of NFPA No. 70, the National Electrical Code.

42. REQUIREMENTS OF NATIONAL ELECTRICAL CODE. Attention should be specifically directed to the requirements of NFPA No. 70, the National Electrical Code, for the location of transformers, type and location of motors, generators and their control equipment, cables, fuses, circuit breakers, conduits and lights of all types.

43. SPECIAL PROVISIONS. Provision should be made for remote control of the electrical circuits so that the current for light and power in any dust-making building may be cut off by switches outside of the building at a distance of at least 4 feet from the nearest doorway. It should also be arranged that the power of the whole plant can be cut off by switches located at one or more central points, such as the office, watchman's booth, etc. All electrical equipment shall be inspected and cleaned periodically. Where flash lights or storage battery lamps are used, they should be of a type approved for the purpose.

Chapter 5. Control of Static Electricity.

51. GROUNDING MACHINERY TO REMOVE STATIC ELECTRICITY produced in dust making and collecting is vital for safety. It should be thoroughly done according to the recommendations of NFPA No. 77M, Static Electricity, not only for stamp mortars or other mills, fans and conveyors in all parts of the plant where dust is made or handled, but also for all dust screens, cyclone collectors, stocking or bag collectors, and screen-cloth collectors. These several kinds of cloth collectors and screens, if not themselves metallic, should have fine non-insulated, non-ferrous wire enmeshed or woven with the cloth, or otherwise securely fastened into it at suitable intervals, and grounded.

Chapter 6. Prevention of Accumulation of Aluminum Powder or Dust.

61. DUST SHALL NOT BE PERMITTED TO ACCUMULATE. Good housekeeping is a factor of utmost importance. To this end an adequate vacuum sweeping system is recommended, although soft push brooms may be used. When vacuum cleaners are employed the only permissible arrangement is where the hose and tools are connected with a system of evacuating tubes to the outside of the building. Each time the stamps or other dust-making machines are charged and/or discharged all dust and other material spilled on open surfaces of the machinery or the floor of the building shall be promptly and thoroughly removed. When vacuum cleaners are employed bulk accumulation of powder and material shall be removed by soft push brooms and non-sparking scoops before the vacuum sweeping equipment is used.

62. COMPETENT SUPERVISION AND PERIODIC CLEANING should always be maintained and the foremen should be alert to prevent the accumulation of excessive dust on any portions of buildings or machinery which are not regularly cleaned in daily operations. Regular periodic cleaning, with all machinery idle and power off, should be carried out as often as local conditions require it to maintain safety, but in any case at least once a week.

63. LOCATION OF DISCHARGE RECEPTACLES OF DUST COLLECTORS: The dust collected by vacuum cleaner nozzles or brushes or otherwise and drawn through an evacuating pipe shall be discharged into a suitable receptacle located outside the dust-making building. Each piece or group of such equipment shall be surrounded with a tight, strong steel shield, preferably cylindrical, open at the top and closed at the bottom and designed to withstand an internal pressure of 200 pounds per square inch, so that if an explosion should occur in dust-collecting receptacles, its full force and flame would be diverted upwardly.

64. FANS AND OTHER EQUIPMENT for moving the air shall be so placed that the entrance of dust is minimized, or else enclosed as above specified. They should have ball or roller bearings, and when used for pneumatic conveying of dust from a machine or group of machines, they should be electrically interlocked with the power supply for such machines, so that in case the fan stops, the machine will stop making dust.

Chapter 7. Prevention of Ignition of Aluminum Powder.

71. GENERAL PRECAUTIONS: In the operation of the plant, every precaution shall be taken to avoid the production of sparks from electrical faults or from either static electricity or sparks caused by impact, such as that of steel or iron articles or stones upon each other or upon concrete. The leakage of water in or into any building where it can come into contact with any aluminum powder shall be prevented to avoid spontaneous heating and ignition therefrom. The electrical heating to a high temperature of any wire or resistance element in a dusty or dust-producing building and the development of serious local heating in machinery, due to friction, should likewise be prevented. The installation of thermostats connected by relays with bell or other indicators may be advisable in some parts of the plant.

72. REMOVAL OF TRAMP METAL AND STRAY PEBBLES: Approved magnetic separators of the permanent magnet or self-cleaning electro-magnetic types or approved pneumatic separators should be installed in an approved manner ahead of all mills, stamps or pulverizers to remove tramp metal from the pieces of aluminum going to the mills or stamps and these pieces should also be carefully examined to remove pebbles or other foreign material which might in subsequent operations produce frictional sparks of sufficient intensity to ignite the aluminum powder.

73. BALL OR ROLLER BEARINGS properly sealed against dust shall be used generally for line shafts or other high-speed equipment, instead of plain bearings, because of the difficulty of maintaining proper lubrication of the latter for preventing their heating. Any open bearings which have to be used should be protected as thoroughly as possible against the ingress of aluminum dust, and on high-speed equipment should be equipped with automatic hot journal alarms.

74. CYCLONE AND BAG COLLECTORS should be equipped with suitable instruments for recording the temperature therein, and with an indicating device to give warning when a dangerous degree of heating is reached. Polishing equipment should also be equipped with temperature recording instruments, to indicate to the operators any tendency toward excessive heating. All such temperature recording instruments should preferably give their indications and make their record at easily observed central locations, so the men in responsible charge may receive warning and take action to remedy the hazardous conditions.

75. NO OPEN FLAMES NOR ELECTRIC OR GAS CUTTING OR WELDING EQUIPMENT shall be permitted within the buildings housing the powder producing or handling machinery during operation. If it becomes absolutely necessary to use such equipment for making repairs all machinery in the room or section of the building where the repairs are to be made shall be shut down and the entire room or section with its machinery shall be thoroughly cleaned to remove all accumulations of aluminum powder. Operators of cutting or welding torches should be required to obtain a permit from the safety or fire protection officer of the plant before using their equipment under any condition around aluminum powder plants. Attention is called to the hazardous conditions that may exist either inside or outside of the plant if cutting torches are used in dismantling dust collectors or powder-producing machinery before all dust accumulations have been removed.

a. **POWDER-OPERATED TOOLS:** Gun-type tools using powder or cartridges for driving pegs or pins into concrete, brick, steel, etc., shall not be used where flammable dust or dust clouds are present. When the use of this type of equipment becomes necessary all dust-producing machinery in the area shall be shut down, all equipment, floors and walls shall be carefully cleaned, and all dust accumulations removed. A careful check shall be made to be sure that no cartridges or charges are left on the premises where they could enter equipment or be accidentally discharged after operation of the dust-producing or handling machinery is resumed.

76. ALUMINUM, COPPER OR BRONZE METAL TOOLS, INCLUDING SHOVELS, and not iron or other spark-producing tools, should be used in any dust-making building except when that part of the plant is stopped, and then only after thorough removal of dust accumulation. This rule should also be followed in dismantling either inside or outside of the plant any discarded powder-producing equipment that may contain dust accumulations.

77. HEATING AND DRYING SHOULD BE DONE ONLY BY HOT AIR, the air to be heated by steam or hot water coils in a small offset to the building. In buildings which may have aluminum dust in them, the heating and drying air should be forced by blower fans into each respective building through a heating unit. In the case of dusty buildings, the fans should draw in their air supply from the outside in order that no explosive dust accumulates in the heating chamber.

78. POWDER OR DUST SWEEPINGS and other materials swept from the floor, machines, or other locations must be carefully screened to remove foreign matter before being placed in any machine for additional fabrication.

79. STARTING MACHINERY AFTER SHUTDOWN: All machines should be thoroughly cleaned and be absolutely dry before they are charged with metal and placed in operation.

Chapter 8. Aluminum Powder Storage.

81. The aluminum powder product, the conveyance of which is referred to in Article 32, and the collection of which is to be in a separate building from the dust-making building, should be packed into steel drums as soon as possible, and these drums tightly sealed and stored in a dry location until they are ready to be shipped from the plant or repacked. Open bin storage is dangerous.

Chapter 9. Fire Fighting Methods for Prevention of Aluminum Powder Explosions.

91. THE USE OF FINE DRY SAND, preferably that screened through a 20-mesh sieve, is at present the best known method of fighting incipient fires of aluminum powder. Water streams or liquid sprays of various kinds that vaporize quickly are highly dangerous, as shown in many instances, since the dust is thrown into the air and the ignited particles instantly cause a violent explosion of the dust. For the same reason, any mechanical agitation or disturbance of the burning powder or that adjacent thereto must be avoided. An ample supply of dry fine-screened sand or other approved powder should be kept in covered bins or covered receptacles each containing about a cubic yard. These receptacles should be placed at a sufficient number of suitable points at or in each building, convenient to reach quickly. The receptacles should be covered and arranged so that the sand can be quickly scooped up by bucket or shovel. These implements shall be made of aluminum or other non-ferrous material.

92. IN FIGHTING AN ALUMINUM POWDER FIRE AVOID STIRRING IT: All electric power should be first shut off; then if the aluminum powder is burning quietly in a place where it can be safely isolated, the sand should be carefully ringed around but not dropped on the burning powder, great care being taken to avoid fanning the dust into the air. The powder, when burning quietly forms a crust which excludes oxygen and gradually extinguishes itself. As soon as the isolation of the fire has been accomplished, the room should be closed, the windows shut, the bottoms of the doors sealed with sand, and the fire allowed to burn itself out.

93. FIRE FIGHTING ORGANIZATION — WATER AND OTHER EXTINGUISHERS MUST NOT BE USED: It is recommended that only those men familiar with, and trained to combat the conditions existing, be permitted near the area involved by a fire. All liquid, carbon dioxide or foam type fire extinguishers should be rigidly excluded from the operating plant to prevent their being used by excited and inexperienced persons during an emergency. Local town or city firemen, who might be called to the plant in case of fire, should be thoroughly instructed in the dangers of using jets of carbon dioxide, water, carbon tetrachloride or other liquids in an aluminum dust fire. They should receive positive orders from their superiors by prior arrangement with the respective officials, forbidding such use in combating any fire in the aluminum powder plant.