



AEROSPACE MATERIAL SPECIFICATION

AMS3195**REV. G**

Issued 1957-07
Reaffirmed 2003-11
Revised 2014-05

Superseding AMS3195F

Silicone Rubber Sponge
Closed Cell, Medium

RATIONALE

This document is being revised through a limited scope ballot to remove incorrect paragraph references.

1. SCOPE

1.1 Form

This specification covers a silicone rubber sponge in the form of sheet, strip, extrusions, and molded shapes.

1.2 Application

This product has been used typically for general applications requiring closed-cell, medium sponge rubber that will be flexible from -103 to +401 °F (-75 to +205 °C), but usage is not limited to such applications. Compression set may be high at the higher temperature.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2810 Identification and Packaging, Elastomeric Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3195G>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D 746 Standard Test Method for Brittleness Temperature of Plastics and Elastomers by Impact

ASTM D 1056 Standard Specification for Flexible Cellular Materials - Sponge or Expanded Rubber

3. TECHNICAL REQUIREMENTS

3.1 Material

Shall be a compound, based on a silicone rubber, suitably cured to produce a product meeting the requirements of 3.2 and 3.3.

3.2 Finish

The top and bottom surfaces of sheet and strip and the exterior surfaces of molded parts and extrusions (except ends) shall have a natural finish.

3.3 Properties

The product shall conform to the requirements shown in Table 1, tests shall be performed on the product supplied and in accordance with ASTM D 1056, except as otherwise specified herein:

TABLE 1 - PROPERTIES

Paragraph	Test	Requirement	Test Method
3.3.1	Compression-Deflection	6 to 14 psi (41.3 to 96.5 kPa)	77 °F ± 9 (25 °C ± 5)
3.3.2	Density, maximum		
	Nominal Thickness		
3.3.2.1	Under 0.25 inch (6.35 mm)	0.025 pounds/cubic inch (0.69 g/cm ³)	
3.3.2.2	0.25 inch (6.35 mm) and over	0.020 pounds/cubic inch (0.55 g/cm ³)	
3.3.3	Compression Set		212 °F ± 2 (100 °C ± 1)
3.3.3.1	Percent of Original Deflection, maximum	60%	22 hours ± 0.2
3.3.4	Brittleness Temperature, maximum	-67 °F (-55 °C)	ASTM D 746

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall be as shown in Table 2 and Table 3; measurements shall be made in accordance with ASTM D 1056:

3.5.1 Sheet and Strip

3.5.1.1 Thickness

TABLE 2A - TOLERANCES, INCH/POUND UNITS

Nominal Thickness Inch			Tolerance Inch plus	Tolerance Inch minus
Up	to	0.063, inclusive	0.030	0.016
Over	0.063 to	0.188, inclusive	0.030	0.030
Over	0.188 to	0.313, inclusive	0.050	0.030
Over	0.313 to	0.500, inclusive	0.060	0.060
Over	0.500 to	0.750, inclusive	0.090	0.090
Over	0.750		0.120	0.120

TABLE 2B - TOLERANCES, SI UNITS

Nominal Thickness Millimeters			Tolerance Millimeters plus	Tolerance Millimeters minus
Up	to	1.60, inclusive	0.76	0.41
Over	1.60 to	4.78, inclusive	0.76	0.76
Over	4.78 to	7.95, inclusive	1.27	0.76
Over	7.95 to	12.70, inclusive	1.52	1.52
Over	12.70 to	19.05, inclusive	2.29	2.29
Over	19.05		3.05	3.05

3.5.1.2 Length and Width

TABLE 3A - TOLERANCES, INCH/POUND UNITS

Nominal Length and Width Inches			Tolerance, Inch plus and minus
Up	to	6, inclusive	0.125
Over	6 to	18, inclusive	0.250
Over	18		0.375

TABLE 3B - TOLERANCES, SI UNITS

Nominal Length and Width Millimeters			Tolerance, Millimeters plus and minus
Up	to	152, inclusive	3.18
Over	152 to	457, inclusive	6.35
Over	457		9.52

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of sponge shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sponge conforms to specified requirements.

4.2 Classification of Tests

Tests for all technical requirements are acceptance tests and preproduction tests and shall be performed prior to or on the initial shipment of sponge to a purchaser, on each lot, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 For Acceptance Tests

Sufficient sponge shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all sponge produced from the same batch of compound, processed in one continuous production run, and presented for vendor's inspection at one time. An inspection lot shall not exceed 500 pounds (227 kg).

4.3.1.2 A batch shall be the quantity of compound run through a mill or mixer at one time.

4.3.1.3 When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5 shall state that such plan was used.

4.3.2 For Preproduction Tests

As agreed upon by purchaser and vendor.

4.4 Approval

4.4.1 Sample sponge shall be approved by purchaser before sponge for production use is supplied, unless such approval be waived by purchaser. Results of tests on production sponge shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production sponge which are essentially the same as those used on the approved sample sponge. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for re-approval a statement of the proposed changes in ingredients and/or processing and, when requested, sample sponge. Production sponge made by the revised procedure shall not be shipped prior to receipt of re-approval.

4.5 Reports

The vendor of sponge shall furnish with each shipment a report showing the results of tests to determine conformance to the technical requirements. This report shall include the purchase order number, vendor's compound number, lot number, AMS3195G, form or part number, and quantity.

4.6 Resampling and Retesting

If any specimen used in the above tests fails to meet the specified requirements, disposition of the sponge may be based on the results of testing three additional specimens from the same lot for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the sponge represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY

5.1 Identification and Packaging

Shall be in accordance with AMS2810.

5.1.1 A lot may be packaged in small quantities and delivered under the basic lot approval provided lot identification is maintained.

6. ACKNOWLEDGMENT

A supplier shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.