



AEROSPACE MATERIAL SPECIFICATION

AMS3901/17

REV. B

Issued 1996-02
Revised 2008-12
Reaffirmed 2014-07

Superseding AMS3901/17A

Yarn, Organic Fiber (Para-Aramid), High Modulus
720 Denier, (800 d tex), 1.2% Finish

RATIONALE

AMS3901/17B has been reaffirmed to comply with the SAE five year review policy.

1. SCOPE

1.1 Form

This specification covers one type of organic fiber in the form of yarn. The product shall be formed as a multiplicity of filaments drawn together and gathered into an approximately parallel arrangement.

1.2 Classification

Organic 720 denier (800 d tex) yarn with 390 ksi (2689 MPa) or 21.0 g/d minimum nominal tensile strength and 16.5 Msi (114 GPa) or 900 g/d minimum tensile modulus for use in weaving requiring high tensile strength and high modulus of elasticity in tension.

2. APPLICABLE DOCUMENTS

The following publications form a part of this document to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order. In the event of conflict between the text of this document and references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

2.1 SAE Publications:

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001. Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org

AMS3901 Organic Fiber (Para-Aramid), Yarn and Roving, High Modulus

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3901/17B>

3. TECHNICAL REQUIREMENTS

3.1 Basic Specification

The complete requirements for procuring the organic yarn described herein shall consist of this document and the latest issue of the basic specification.

3.2 Properties

Shall be as shown in Table 1; no individual package, based on the average of five determinations, shall have less than 90% of the lot minimum values specified in 3.2.1 and 3.2.2.

TABLE 1 - PROPERTIES

Paragraph	Requirement	Requirement Dry Twisted Yarn	Requirement Impregnated Strand	Test Method
3.2.1	Tensile Strength, min	21.0 g/d	390 ksi (2689 MPa)	4.5.1 of AMS 3901
3.2.2	Modulus of Elasticity, min	900 g/d	16.5 Msi (114 GPa)	4.5.1 of AMS 3901
3.2.3	Linear Density	720 $\pm$ 25 denier (800 $\pm$ 25 d tex)	720 $\pm$ 25 denier (800 $\pm$ 25 d tex)	4.5.2 of AMS 3901
3.2.4	Fiber Finish, by weight	1.2% $\pm$ 0.6	1.2% $\pm$ 0.6	4.5.3 of AMS 3901
3.2.5	Fiber Density	0.052 pound mass per cubic inch $\pm$ 0.001 (1.44 grams/cm ³ $\pm$ 0.03)	0.052 pound mass per cubic inch $\pm$ 0.001 (1.44 grams/cm ³ $\pm$ 0.03)	

3.3 Splicing

There shall be no knots or splices in the continuous yarn.

4. QUALITY ASSURANCE PROVISIONS

Shall be in accordance with AMS3901.

5. PREPARATION FOR DELIVERY

Shall be in accordance with AMS3901.

6. ACKNOWLEDGMENT

Shall be in accordance with AMS3901.

7. REJECTIONS

Shall be in accordance with AMS3901.