



Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 5627C
Superseding AMS 5627B

Issued 2-15-52
Revised 4-1-81

UNS S43000

STEEL BARS, FORGINGS, TUBING, AND RINGS, CORROSION AND MODERATE HEAT RESISTANT
17Cr (SAE 51430)
Annealed

1. SCOPE:

- 1.1 **Form:** This specification covers a corrosion and moderate heat resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.
- 1.2 **Application:** Primarily for parts and assemblies, such as turbine air seals, requiring oxidation resistance up to 1600°F (870°C) but useful at the higher temperatures only when strength requirements are moderately low.

2. **APPLICABLE DOCUMENTS:** The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 **SAE Publications:** Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing
- AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steel and Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Product Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings
- AMS 7493 - Rings, Flash Welded, Non-Austenitic Corrosion Resistant Steels

- 2.2 **ASTM Publications:** Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E112 - Estimating the Average Grain Size of Metals
- ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Similar Chromium-Nickel-Iron Alloys

- 2.3 **U.S. Government Publications:** Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.12
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	16.00 -	18.00
Nickel	--	0.75
Molybdenum	--	0.50
Copper	--	0.50
Aluminum	--	0.05
Tin	--	0.05

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A370:

- 3.2.1 Bars: Annealed having hardness not higher than 202 HB or equivalent.

- 3.2.1.1 All hexagons and other bars 0.500 - 2.750 in. (12.50 - 70 mm), incl, in nominal diameter or distance between parallel sides shall be cold finished.

- 3.2.1.2 Bars, other than hexagons, over 2.750 in. (70 mm) in nominal diameter or distance between parallel sides shall be hot finished.

- 3.2.2 Wire: Cold drawn and annealed having tensile strength not higher than 100,000 psi (690 MPa) or equivalent hardness.

- 3.2.3 Forgings and Flash Welded Rings: Annealed having hardness not higher than 183 HB or equivalent.

- 3.2.3.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7493.

- 3.2.4 Mechanical Tubing: Annealed and cold finished having hardness not higher than 202 HB or equivalent.

- 3.2.5 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash ring manufacturer.

- 3.3 Properties: The product shall conform to the following requirements:

- 3.3.1 Grain Size: Bars, wire, forgings, tubing, and stock for flash welded rings shall have grain size not larger than 0, determined by comparison of a polished and etched specimen with the chart in ASTM E112. Grain size of flash welded rings shall be as agreed upon by purchaser and vendor.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars, wire, and tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of the following:

3.6.1 Bars and Wire: AMS 2241.

3.6.2 Mechanical Tubing: AMS 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Flash Welded Rings: AMS 2371.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition and grain size of each heat. This report shall include the purchase order number, AMS 5627C, heat number, size, and quantity from each heat. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5627C, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with the following: