

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS5694A

Issued 9-1-48

Revised 6-1-51

STEEL WIRE, CORROSION AND HEAT RESISTANT 25Cr - 20Ni (30310)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for use as bare wire filler metal for welding.

3. COMPOSITION:

			Check Analysis	
			Under Min or Over Max	
Carbon	0.15 max	--		0.01
Manganese	1.25 - 2.50	0.04		0.04
Silicon	0.25 - 0.60	0.05		0.05
Phosphorus	0.040 max	--		0.005
Sulfur	0.030 max	--		0.005
Chromium	26.50 - 28.00	0.25		0.25
Nickel	21.00 - 22.50	0.20		0.20
Molybdenum	0.50 max	--		0.03
Copper	0.50 max	--		0.03

4. CONDITION: Cold drawn, unless otherwise specified.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties: Wire furnished in coils shall have tensile strength of 125,000 - 150,000 psi.

5.2 Weldability: Melted wire shall flow smoothly and evenly during welding and shall be capable of producing acceptable welds.

6. QUALITY: Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external defects detrimental to its use for welding purposes.

7. TOLERANCES:

7.1 Unless otherwise specified, straight lengths shall not vary in length more than plus and minus 1/4 in. from the length ordered.

7.2 Unless otherwise specified, diameter of the wire shall not vary more than plus and minus 0.002 in. from the size ordered.

8. REPORTS

8.1 Unless otherwise specified, the vendor of wire shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."