



AEROSPACE MATERIAL SPECIFICATION

AMS5755**REV. G**

Issued 1957-01
Reaffirmed 2007-04
Revised 2014-04

Superseding AMS5755F

Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, and Rings
64Ni - 5.0Cr - 24.5Mo - 5.5Fe
Solution Heat Treated
(Composition similar to UNS N10004)

RATIONALE

AMS5755G revises Condition (3.2.2) and Reports (4.4), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application

These products have been used typically for parts requiring oxidation resistance up to 1600 °F (871 °C), good strength up to 1200 °F (649 °C), and low coefficient of expansion, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2261 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire

AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys

AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5755G>**

AMS2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2750	Pyrometry
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AMS7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation Hardenable Alloys

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 10	Brinell Hardness of Metallic Materials
ASTM E 21	Elevated Temperature Tension Tests of Metallic Materials
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 – COMPOSITION

Element	min	max
Carbon	--	0.12
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	4.00	6.00
Molybdenum	23.00	26.00
Iron	4.00	7.00
Vanadium	--	0.60
Cobalt (3.1.1)	--	2.50
Nickel + Cobalt	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars

Hot rolled, solution heat treated, and descaled. Rounds 0.75 inch (19.0 mm) and over in nominal diameter shall be ground.

3.2.1.1 Bars shall not be cut from plate (See also 4.4.2).

3.2.2 Forgings

Solution heat treated and descaled.

3.2.3 Flash Welded Rings

Solution heat treated.

3.2.3.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS7490.

3.2.4 Stock for Forging or Flash Welded Rings

As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment

Bars, forgings, and flash welded rings shall be solution heat treated by heating to $2150^{\circ}\text{F} \pm 25$ ($1177^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with section thickness but not less than 20 minutes, and cooling at a rate equivalent to a rapid air cool or faster. Pyrometry shall be in accordance with AMS2750.

3.4 Properties

The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings

3.4.1.1 Tensile Properties at 1500°F (816°C)

Shall be as shown in Table 2, determined in accordance with ASTM E 21 on specimens heated to $1500^{\circ}\text{F} \pm 5$ ($816^{\circ}\text{C} \pm 3$), held at heat for 20 to 30 minutes before testing, and tested at $1500^{\circ}\text{F} \pm 5$ ($816^{\circ}\text{C} \pm 3$):

TABLE 2 – MINIMUM ELEVATED TEMPERATURE TENSILE PROPERTIES

Property	Value
Tensile Strength	55 ksi (379 MPa)
Elongation in 4D	10%

3.4.1.2 Hardness

Shall be 170 to 241 HB, or equivalent (See 8.2), determined in accordance with ASTM E 10.

3.4.2 Stock for Forging or Flash Welded Rings

As agreed upon by purchaser and vendor.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances

Bars shall conform to all applicable requirements of AMS2261.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Tests for the following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Elevated temperature tensile properties (3.4.1.1) and hardness (3.4.1.2) of each lot of bars, forgings, and flash welded rings.

4.2.1.3 Tolerances (3.6) of bars.

4.2.2 Periodic Tests

Tests to determine ability of stock for forging or flash welded rings to develop required properties (3.4.2) and tests for grain flow of die forgings (3.5.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Flash Welded Rings, and Stock for Forging or Flash Welded Rings

In accordance with AMS2371.

4.3.2 Forgings

In accordance with AMS2374.

4.4 Reports

4.4.1 The vendor of bars, forgings, and flash welded rings shall furnish with each shipment a report showing the vendor's name and country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations) and showing the results of tests for composition of each heat, for elevated temperature tensile properties and hardness of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5755G, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.